



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND



Protective & Marine Coatings

MACROPOXY™ M922 EPOXY GLASS FLAKE

FORMERLY KNOWN AS EPIGRIP M922 / TRANSGARD TG123

Revised 05/2019 Issue 34

PRODUCT INFORMATION

PRODUCT DESCRIPTION

A high solids 2-pack epoxy containing micronised glass flake and anti-corrosive pigments.

RECOMMENDED USE

Corrosion protection of blast cleaned steel and cathodically protected steel.

Possess excellent abrasion resistance and has excellent resistance to immersion in sea water and a range of chemicals also compatible with cathodic protection.

Aluminium Macropoxy M922M mastic version available for high build brushing maintenance specifications.

ENDORSEMENTS

Approved to Def Stan 80-97 Treatment of Fuel Tanks.
Highways Agency Item No. 123
Network Rail Item No. 7.2.3
Approved for carriage of grain
Complies with NORSOK M501 Rev. 5 System 7

RECOMMENDED APPLICATION METHODS

Airless Spray
Brush

Recommended Cleanser Thinner: No 9

PRODUCT CHARACTERISTICS

Flash Point: Base 9°C Additive 23°C

% Solids by Volume: 83 ± 4% (ASTM-D2697-03(2014))

Pot Life: 3hrs @5°C 1½hrs @ 15°C 1hr @ 23°C

Colour Availability: Limited Range

VOC

143 gms/litre determined practically in accordance with UK Regulations PG/23
167 gms/litre calculated from formulation to satisfy EC Solvent Emissions Directive
107 gms/kilo content by weight from formulation, to satisfy EC Solvent Emissions Directive

RECOMMENDED THICKNESS

Dry film thickness	Wet film thickness	Theoretical coverage
400 microns	482 microns	2.1m ² /ltr*

* This figure makes no allowance for surface profile, uneven application, overspray or losses in containers and equipment. Film thickness will vary depending on actual use and specification.

PRACTICAL APPLICATION RATES-MICRONS PER COAT

	Airless Spray	Brush
Dry	400*	250
Wet	482	302

* Maximum sag tolerance typically 1200µm wet (1000µm dry) by airless spray.

AVERAGE DRYING TIMES

	@ 5°C	@ 15°C	@ 23°C
To touch:	12 hours	6 hours	4 hours
To recoat:	6 hours	4 hours	3 hours
To handle:	30 hours	16 hours	8 hours

These figures are given as a guide only. Factors such as air movement and humidity must also be considered.

RECOMMENDED PRIMERS

Primers are optional. M922 can be applied directly onto steel.
Macropoxy M111 Wet Blast Primer
Macropoxy L574 Blast Primer
Macropoxy L674 Blast Primer
Please consult Sherwin-Williams for guidance on alternative primers.

RECOMMENDED TOPCOATS

Indefinitely self overcoatable provided the coating has been suitably cleaned. For optimum intercoat adhesion with other epoxy topcoats, overcoating should occur within 14 days. Where atmospheric exposure is required overcoat with Acrolon C137V2, Acrolon C237, Acrolon 1850 and Acrolon 7300 within 7 days at a minimum d.f.t. of 50 microns or in the case of Acrolon C750V2 overcoat within 4 days.

These overcoating times refer to achievement of optimum adhesion at 23°C and will vary with temperature.

PACKAGE

A two component material supplied in separate containers to be mixed prior to use

Pack Size: 20 litre and 4 litre units when mixed

Mixing Ratio: 3 parts base to 1 part additive by volume

Weight: 1.59 kg/litre (may vary with shade)

Shelf Life: 2 years from date of batch manufacture



Protective & Marine Coatings

MACROPOXY™ M922 EPOXY GLASS FLAKE

FORMERLY KNOWN AS EPIGRIP M922 / TRANSGARD TG123

Revised 05/2019 Issue 34

PRODUCT INFORMATION

SURFACE PREPARATION

Blast clean to Sa2½ ISO 8501-1:2007 using angular grit. Average surface profile in the range 50-100 microns.

For agreed maintenance specifications, M922 may be applied onto manually prepared surfaces to a minimum standard of St3 ISO8501-1:2007 Part A1. Please consult Sherwin-Williams to confirm specification.

Ensure surfaces to be coated are clean, dry and free from all surface contamination.

Macropoxy L574 should be specified where there is a requirement for a blast primer. Other blast primers should not be used without reference to Sherwin-Williams.

APPLICATION EQUIPMENT

Airless Spray

Nozzle Size	:	0.38-0.53mm (15-21 thou)
Fan Angle	:	65°
Operating Pressure	:	210kg/cm ² (3000 psi)

The airless spray details given above are intended as a guide only. Details such as fluid hose length and diameter, paint temperature and job shape and size all have an effect on the spray tip and operating pressure chosen. However, the operating pressure should be the lowest possible consistent with satisfactory atomisation. As conditions will vary from job to job, it is the applicators' responsibility to ensure that the equipment in use has been set up to give the best results. If in doubt Sherwin-Williams should be consulted.

APPLICATION CONDITIONS AND OVERCOATING

In conditions of high relative humidity, ie. 80-85% good ventilation conditions are essential. Substrate temperature shall be at least 3°C above the dew point and always above 0°C.

At application temperatures below 10°C, drying and curing times will be significantly extended, and spraying characteristics may be impaired.

Application at ambient air temperatures below 5°C is not recommended.

If it is desired to overcoat outside the times stated on the data sheet, please seek advice of Sherwin-Williams.

Brush

Macropoxy M922 is capable of being applied by brush at 250 microns dft.

It is possible to apply Macropoxy M922 onto a damp substrate (no running or pooled water) by brush application. Ensure that the paint fully displaces any water on the substrate.

Macropoxy M922 may be applied by brush onto hot surfaces up to 120°C. Multiple coats will be necessary to achieve required film build. Ensure good ventilation and adequate PPE due to rapid vapourisation of solvent from the film at high temperatures.

ADDITIONAL NOTES

Drying times, curing times and pot life should be considered as a guide only.

The curing reaction of epoxies commences immediately the two components are mixed, and since the reaction is dependent on temperature, the curing time and pot life will be approximately halved by a 10°C increase in temperature and doubled by a 10°C decrease in temperature.

Material is not suitable for force drying above 50°C.

Epoxy Coatings - Colour Stability:

Variable colour stability is a feature of epoxy materials which tend to yellow and darken with age. Therefore any areas touched-up and repaired with the same colour at a later date may be obvious due to this colour change.

When epoxy materials are exposed to ultra-violet light a surface chalking effect will develop. This phenomenon results in loss of gloss and a fine powder coating at the surface which may give rise to colour variation depending on the aspect of the steelwork. This effect in no way detracts from the performance of the system.

Epoxy Coatings - Tropical Use

Epoxy paints at the time of mixing should not exceed a temperature of 35°C. At this temperature the pot life will be approximately halved. Use of these products outside of the pot life may result in inferior adhesion properties even if the materials appear fit for application. Thinning the mixed product will not alleviate this problem.

The maximum air and substrate temperature for application is 50°C providing conditions allow satisfactory application and film formation. If the air and substrate temperatures exceed 50°C and epoxy coatings are applied under these conditions, paint film defects such as dry spray, bubbling and pinholing etc. can occur within the coating.

Numerical values quoted for physical data may vary slightly from batch to batch.

HEALTH AND SAFETY

Consult Product Health and Safety Data Sheet for information on safe storage, handling and application of this product.

WARRANTY

Any person or company using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk, and Sherwin-Williams can accept no liability for the performance of the product, or for any loss or damage arising out of such use.

The information detailed in this Data Sheet is liable to modification from time to time in the light of experience and of normal product development, and before using, customers are advised to check with Sherwin-Williams, quoting the reference number, to ensure that they possess the latest issue.