



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

SIGMASHIELD™ 880 / AMERLOCK® 880

DESCRIPTION

Two-component, high-build, polyamine adduct-cured epoxy coating

PRINCIPAL CHARACTERISTICS

- Primarily designed for use in offshore splash zone maintenance
 - Outstanding sea water resistance
 - Excellent corrosion resistance
 - Surface tolerant and abrasion resistant
 - Continues to cure when immersed in water
 - Long-term protection in a single-coat application
 - Resistant to well designed cathodic protection
 - Suitable for application on exterior of buried pipes
 - Suitable on wet blast or ultra high pressure water (UHPWW) cleaned substrates (damp or dry)
 - Suitable primer for SIGMAGLIDE fouling release system
-

COLOR AND GLOSS LEVEL

- Offwhite, yellow and black (other colors available on request)
- Gloss

Note:

- Epoxy coatings will characteristically chalk and fade upon exposure to sunlight. Light colors are prone to ambering to some extent in interior or exterior exposures
-

SIGMASHIELD™ 880 / AMERLOCK® 880

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.5 kg/l (12.1 lb/US gal)
Volume solids	85 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 122.0 g/kg UK PG 6/23(92) Appendix 3: max. 207.0 g/l (approx. 1.7 lb/US gal) EPA Method 24: 200.0 g/ltr (1.7 lb/USgal) China GB 30981-2020 (tested) 152.0 g/l (approx. 1.3 lb/gal)
Recommended dry film thickness	150 - 1000 µm (6.0 - 40.0 mils) depending on system
Theoretical spreading rate	4.3 m ² /l for 200 µm (170 ft ² /US gal for 8.0 mils)
Dry to touch	3 hours
Overcoating Interval	Minimum: 3.5 hours Maximum: 14 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Coating performance will depend upon the surface preparation degree
- For atmospheric service, abrasive blast to ISO-Sa2½ or minimum SSPC SP-6, power tool cleaned to ISO-St3 (SSPC SP-3) or hand tool cleaned to ISO-St2 (SSPC SP-2) or ultra high pressure water jet to SSPC SP WJ-2(L) / NACE WJ-2(L)
- For immersion service: steel; blast cleaned to ISO-Sa2½ (SSPC SP-10), blasting profile 40 – 75 µm (1.6 – 3.0 mils)
- SSPC SP WJ-2(L) is also acceptable over a previous blasted surface
- For touch up and repair, power tool cleaning in accordance with SSPC SP-11 is acceptable
- Higher profiles (>75 microns, 3.0 mils) is allowable with appropriate coating thickness
- Compatible previous coat must be dry and free from any contamination

Note:

- Coating performance is, in general, proportional to the degree of surface preparation.

SIGMASHIELD™ 880 / AMERLOCK® 880

Galvanized, stainless steel and non-ferrous metals

- Galvanised steel; sweep blasted or otherwise roughened; dry and free from salts and other contamination
- Stainless steel and non-ferrous metal; degreased and sweep blast, SSPC SP-16 with blasting profile 40 – 100 µm (1.5 – 4.0 mils)
- The surface should be sufficiently roughened by sweep blasting with inert non-metallic abrasives

Substrate temperature and application conditions

- Substrate temperature during application should be at least 3°C (5°F) above dew point

INSTRUCTIONS FOR USE

mixing ratio by volume: base to hardener 75:25 (3:1)

- Thinner should be added after mixing the components
- Do not thin more than is required by appropriate application property
- Adding too much thinner results in reduced sag resistance and slower cure

Pot life

2 hours at 20°C (68°F)

Note:

- See ADDITIONAL DATA – Pot life

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
500 µm (20.0 mils)	1.7 m ² /l (68 ft ² /US gal)
200 µm (8.0 mils)	4.3 m ² /l (170 ft ² /US gal)

Overcoating interval for DFT up to 500 µm (20.0 mils)							
Overcoating with...	Interval	-5°C (23°F)	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	36 hours	14 hours	7 hours	3.5 hours	2 hours	1.5 hours
	Maximum	2 months	1.5 months	1 month	28 days	21 days	14 days

Note:

- Surface should be dry and free from any contamination



SIGMASHIELD™ 880 / AMERLOCK® 880

Overcoating interval for SIGMASHIELD 880 (Marine black) DFT up to 300 µm (12.0 mils)							
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	15°C (59°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
SIGMAGLIDE 790	Minimum	24 hours	20 hours	16 hours	10 hours	6 hours	4 hours
	Maximum	11 days	10 days	9 days	8 days	7 days	6 days

Curing time for DFT up to 500 µm (20 mils)			
Substrate temperature	Full cure	Dry to touch	Dry to handle
-5°C (23°F)	30 days	24 hours	48 hours
5°C (41°F)	18 days	10 hours	24 hours
10°C (50°F)	14 days	5 hours	16 hours
20°C (68°F)	7 days	3 hours	8 hours
30°C (86°F)	5 days	2 hours	5 hours
40°C (104°F)	3 days	1 hour	3 hours

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	3 hours
20°C (68°F)	2 hours
30°C (86°F)	1 hour

Product Qualifications

- Qualified for NORSOK M501 Rev.6 System 7C up to 120°C(250°F) with 175 microns 2 coat system (SIGMASHIELD 880ALU primer), which can be used as NORSOK M501 System 7B as well
- Qualified for NORSOK M501 Rev.6 System 7A with 300 microns 2 coat system (with SIGMASHIELD 880 ALU primer)
- Meets or exceeds the performance requirements of Corps of Engineers C-200a and SSPC Paint 16

SAFETY PRECAUTIONS

- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes
- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets



SIGMASHIELD™ 880 / AMERLOCK® 880

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.