



# New Guard Coatings Group

A global reputation to protect.

**You have acquired this data sheet from the New Guard Coatings Group.**

**All information listed is correct at the time of print.**

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

## PINTURA CLOROCAUCHO SUELOS



### Product Description

Paint industrial floors, indoors and of maximum quality based on chlororubber resins and highly colour fast pigments

### Carta de Colores

[Carta de colores Pinturas para Suelos](#)



### Technical Characteristics

Colour	Chrome green, english red, ral 7038 grey, yellow and white
Appearance	Semi matt
Touch-dry	30 minutes, depending on the thickness applied and atmospheric conditions
Repainting	After 24 hours
Yield	9-12 m <sup>2</sup> /l, per coat, depending on the state and type of surface
Thinner	DILUYENTE CLOROCAUCHOS 300
Storage	Excellent for up to 1 year/s, unopened, in original packaging, at normal temperature and humidity. Store in places protected against frost.

### Properties

- Easy to apply
- Good covering power.
- Filling power
- Finish adherent and decorative
- Resistant to abrasion, wear, washing, chemical attacks and grime in general.
- Prevents the build up of dust, prevents erosion and makes it easy to keep clean

### Applications

Suitable for indoors, concrete floors, cement mortar, other derivatives, garages, sports halls, signposts, washrooms, industrial buildings and car parks.

### Method of Use

- Stir the contents of the pot well
- Apply well ventilated and in thin, even, well-spread coats
- Application at: Round brush and airless spray gun

### Preparation of surfaces

- Surfaces should be sanded, clean, dry and free from dust, grease, oil and moisture.
- Clean floor, dry and well hardened (28 days)
- Residual floor humidity at 6%.
- Preferably rough to improve adherence.
- On unpainted surfaces: Apply the product diluted with rubber paint solvent 300 as preparation, and then a minimum of two coats as described on the container or diluted with Rubber Paint solvent 300 Diluyente Cloro Caucho 300
- On with old paintwork surfaces: Remove damaged paintwork and proceed as for unpainted surfaces

### Recommendations before application

- Do not apply in temperatures below 8°C.
- Relative ambient humidity below 80%

Surface temperature higher than 6°C

**Other data**

Packaging 0.375L, 0.75L, 4L and 15L

**Remarks**

Shake contents of containers before use.  
For toxicological standards, consult FICHA DE SEGURIDAD.  
Do not store opened or started containers.  
Apply with good air renewal.

*This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 25-07-2017 This sheet replaces all previous versions.*