

New Guard Coatings Group

A global reputation to protect.

You have acquired this data sheet from the New Guard Coatings Group.

All information listed is correct at the time of print.



uksales@newguardcoatings.com



+44 1937 586311

Global Head Office: New Guard Coatings Ltd, Sandbeck Way, Wetherby, Leeds, LS22 7DN





Guard Chlor Rubber Line Marking Paint

Description: A chlorinated rubber based road lining paint.

Uses: As a line marking paint principally for concrete surfaces.

Pack Sizes:	Colours:	Thinner:
5 Litre	Yellow (08 E 51) & White. Others available upon request.	Guard Standard Thinner

Theoretical Spreading Rate: 7m² per litre

Volume Solids: 36% (+/-2%)

Dry Film Thickness: (DFT) 50µm

Wet Film Thickness: (WFT) 140µm

Flash Point: 22° C – 32° C

VOC Content: 548 (grams per litre)

Surface Preparation:

Ensure surfaces are clean, dry and free from grease and other contamination before coating. Thoroughly degrease and where applicable, abrade to remove rust and promote good adhesion of the coating. Complex structures may be more effectively cleaned by detergent pressure washing or steam cleaning.

Mixing Instructions:

It is essential that the material is thoroughly mixed before use.

Application:

Brush <input checked="" type="checkbox"/>	Roller <input checked="" type="checkbox"/>	Airless Spray <input type="checkbox"/>	Conventional Spray <input type="checkbox"/>
If required product may be thinned	If required product may be thinned	N/A	N/A

In order to achieve the recommended dft, additional coats may be required depending on the equipment used, spraying techniques and substrate profile.

Drying Times:

Please note drying times are based on temperature at 20°C.

Touch Dry:
30-40 minutes

Recoatable:
N/A

Hard Dry:
3-4 Hours

Storage: Keep material in containers and use within 12 months of delivery. Materials not used should be resealed. Store in a cool, dry place and at temperatures no lower than 10°C.

Precautions: Materials are both hazardous and flammable and therefore precaution measures should be taken and appropriate P.P.E worn in accordance with the Material Safety Data Sheets and regulations.

Health & Safety: Please view the product Health & Safety Sheet for information in relation to hazardous identification, first aid measures, fire fighting, accidental release, handling, exposure control, personal protective equipment (P.P.E), disposal and regulatory information.

Additional Info: The above information should be used as a guide only and is not a guarantee or warranty. New Guard Coatings and our supply partners have provided this information in good faith and is to the best of our knowledge correct at the time of print. 'Guard' is a brand owned by New Guard Coatings Ltd, but this does not imply the manufacture of such product.

Review: Date of Print: March 2014
Last Review:

Contact Information:

UK Head Office:
New Guard Coatings Ltd
Sandbeck Way, Wetherby, West Yorkshire, LS22 7DN

USA Head Office:
New Guard Coatings Inc
615 South Dupont Highway, Dover, DE, 19901

Tel: +44 (0)1937 586311
Email: uksales@newguardcoatings.com

Tel: +1 (302)-257-5760
Email: usasales@newguardcoatings.com

www.newguardcoatings.com