



# New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

# PPG VIKOTE™ 56

## DESCRIPTION

Modified acrylic finish

## PRINCIPAL CHARACTERISTICS

- Finish coat for above-water areas
- Good gloss and color retention
- Resistant to water and splash of mild chemicals
- Fast-drying
- Can be applied at low temperatures, down to -10°C (14°F)

## COLOR AND GLOSS LEVEL

- White and various other colors (see also SIGMACARE shade card)
- Gloss

## BASIC DATA AT 20°C (68°F)

Data for product	
Number of components	One
Mass density	1.1 kg/l (9.2 lb/US gal)
Volume solids	35 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 538.0 g/kg max. 569.0 g/l (approx. 4.7 lb/US gal) China GB 38469-2019 (tested) 595.0 g/l (approx. 5.0 lb/gal)
Recommended dry film thickness	35 µm (1.4 mils)
Theoretical spreading rate	10.0 m <sup>2</sup> /l for 35 µm (401 ft <sup>2</sup> /US gal for 1.4 mils)
Dry to touch	30 minutes
Overcoating Interval	Minimum: 4 hours Maximum: Unlimited
Shelf life	At least 24 months when stored cool and dry

### Notes:

- See ADDITIONAL DATA - Overcoating intervals
- See ADDITIONAL DATA - Curing time

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Substrate conditions

- Previous coat (chlorinated rubber, vinyl or acrylic coatings) must be dry and free from any contamination



# PPG VIKOTE™ 56

## **Substrate temperature and application conditions**

- Substrate temperature during application should be at least 3°C (5°F) above dew point
- 

## **INSTRUCTIONS FOR USE**

- Stir well before use
  - The temperature of the paint should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
  - Adding too much thinner results in reduced sag resistance
  - Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)
- 

### **Air spray**

#### **Recommended thinner**

THINNER 21-06

#### **Volume of thinner**

5 - 10%, depending on required thickness and application conditions

#### **Nozzle orifice**

1.8 - 2.0 mm (approx. 0.070 - 0.079 in)

#### **Nozzle pressure**

0.2 - 0.3 MPa (approx. 2 - 3 bar; 29 - 44 p.s.i.)

---

### **Airless spray**

#### **Recommended thinner**

THINNER 21-06

#### **Volume of thinner**

0 - 5%, depending on required thickness and application conditions

#### **Nozzle orifice**

Approx. 0.28 - 0.33 mm (0.011 - 0.013 in)

#### **Nozzle pressure**

12.0 - 15.0 MPa (approx. 120 - 150 bar; 1741 - 2176 p.s.i.)

---

# PPG VIKOTE™ 56

## Brush/roller

### Recommended thinner

THINNER 21-06

### Volume of thinner

0 – 3%

## Cleaning solvent

THINNER 21-06

## ADDITIONAL DATA

Overcoating interval for DFT up to 35 µm (1.4 mils)			
Overcoating with...	Interval	5°C (41°F)	20°C (68°F)
itself	Minimum	8 hours	4 hours
	Maximum	Unlimited	Unlimited

Curing time for DFT up to 35 µm (1.4 mils)	
Substrate temperature	Dry to touch
5°C (41°F)	1 hour
20°C (68°F)	30 minutes

Color scheme	
PPG VIKOTE 56 colors	PPG VIKOTE 46 colors
7003, 7000, 1188, 3138, 3142	Offwhite
3179, 3149, 4150, 4171, 5163	Offwhite
1188, 1199, 5163, 5177, 6188	Light gray
5177, 5198, 8000	Dark gray
4199	Green
2182, 6179	Redbrown
8000	Black

Note: PPG VIKOTE 56 colors to be applied on top of PPG VIKOTE 46 colors for optimal aesthetics

## SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes



# PPG VIKOTE™ 56

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

## REFERENCES

• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
• DIRECTIVES FOR VENTILATION PRACTICE	INFORMATION SHEET	1434

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgmc.com](http://www.ppgmc.com). The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

