



New Guard Coatings Group

- A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

Technical sheet : RD-Roof Acryl

Description of the product

USE:

Waterborne onecomponent acrylic paint for roofs.

FEATURES:

Very good adhesion - Very good outdoor durability.

SUBSTRATES:

Suits on asbestos-cement roofs, shingles...

Systems

Direct application of 2 coats on the substrate, without primer: the first coat must be diluted with 10% of water.

CONSUMPTION:

Ca. 5 m²/L per coat in function of the porosity of the support

Application instructions

APPLICATION CONDITIONS:

Never apply in heavy sun
Ambient temperature: > 5° C
R.H.: max. 80%

APPLICATION MEANS:

Brush, roller or airless (nozzle: 013-015)

PREPARATION OF THE SUBSTRATE:

The substrate has to be degreased, dry, brushed and the moss must be removed

DILUTION:

Product is ready-for-use.

DRYING TIME (20°C - 68°F):

On touch: 1 hour
Recoatable: 16 hours
By dry and mild conditions, it can be possible to apply 2 coats in one day

CLEANING OF TOOLS:

Water

SPECIFICITIES:

Mix well before use.

Technical data**FINISH:**

Satingloss

COLOURS:

Dark brown, Anthracite grey, Black, Slate grey, Tile red

DENSITY:

1.2 +/- 0.05 g/cm³

SOLIDS CONTENT:

In weight: 50 % +/-2

In volume: 40 % +/-2

VISCOSITY:

80 - 100 P (Brookfield 20RPM)

VOC CONTENT:

< 45 g/L

FLASH POINT:

Not flammable

STORAGE:

24 months, keep away from frost and store away from heat.

Safety data

Information related to hygiene and to safety can be found in the Safety Data Sheet available on request.

These specifications are given for information. Since the manufacturer is not able to check the application of the products, he cannot accept any responsibility for it. This technical data sheet replaces all previous editions.

VERS. R014/230222