



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

SIGMAZINC™ 102 HS

DESCRIPTION

Two-component, high solids polyamide cured zinc rich epoxy primer

PRINCIPAL CHARACTERISTICS

- High build anticorrosive zinc epoxy primer
- Designed as a system primer for various paint systems
- Quick-drying, can be overcoated after a short interval
- Complies with the compositional requirements of SSPC-Paint 20, Level 3

COLOR AND GLOSS LEVEL

- Gray, redbrown
- Flat

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	2.4 kg/l (20.0 lb/US gal)
Volume solids	66 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 120.0 g/kg max. 286.0 g/l (approx. 2.4 lb/US gal) China GB 30981-2020 (tested) 316.0 g/l (approx. 2.6 lb/gal)
Recommended dry film thickness	60 - 150 µm (2.4 - 6.0 mils) depending on system
Theoretical spreading rate	11.0 m ² /l for 60 µm (441 ft ² /US gal for 2.4 mils)
Dry to touch	2 hours
Overcoating Interval	Minimum: 6 hours Maximum: 3 months
Full cure after	7 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA - Spreading rate and film thickness
- See ADDITIONAL DATA - Overcoating intervals
- See ADDITIONAL DATA - Curing time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Immersion exposure

- Steel; shot blast cleaned to ISO-Sa2½, blasting profile 40 - 70 µm (1.6 - 2.8 mils)
- Steel with approved zinc silicate shop primer; sweep blasted to SPSS-Ss



SIGMAZINC™ 102 HS

Atmospheric exposure conditions

- Steel; blast cleaned to ISO-Sa2½, blasting profile 40 – 70 µm (1.6 – 2.8 mils)
 - Steel with approved zinc silicate shop primer; sweep blasted to SPSS-Ss or power tool cleaned to SPSS-Pt3
-

Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
 - Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 80:20 (4:1)

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
 - Adding too much thinner results in reduced sag resistance and slower cure
 - Thinner should be added after mixing the components
-

Induction time

None

Pot life

8 hours at 20°C (68°F)

Air spray

Recommended thinner

THINNER 91-92

Volume of thinner

5 - 15%, depending on required thickness and application conditions

Nozzle orifice

1.8 – 2.2 mm (approx. 0.070 – 0.087 in)

Nozzle pressure

0.3 - 0.6 MPa (approx. 3 - 6 bar; 44 - 87 p.s.i.)

SIGMAZINC™ 102 HS

Airless spray

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.43 – 0.48 mm (0.017 – 0.019 in)

Nozzle pressure

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

Brush/roller

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 10%

Cleaning solvent

THINNER 90-53

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
60 µm (2.4 mils)	11.0 m ² /l (441 ft ² /US gal)
75 µm (3.0 mils)	8.8 m ² /l (353 ft ² /US gal)
100 µm (4.0 mils)	6.6 m ² /l (265 ft ² /US gal)
150 µm (6.0 mils)	4.4 m ² /l (176 ft ² /US gal)

Overcoating interval for DFT up to 100 µm (4.0 mils)					
Overcoating with...	Interval	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
subsequent coating	Minimum	10 hours	6 hours	4 hours	3 hours
	Maximum	3 months	3 months	3 months	3 months

Notes:

- Zinc rich primers can form zinc salts on the surface; preferably they should not be weathered for long periods before overcoating
- An interval of several months can be allowed under clean interior exposure conditions
- Before overcoating any visible surface contamination must be removed by high-pressure water cleaning, sand washing, sweep blasting or mechanical cleaning

SIGMAZINC™ 102 HS

Curing time for DFT up to 100 µm (4.0 mils)			
Substrate temperature	Dry to touch	Dry to handle	Full cure
10°C (50°F)	5 hours	6 hours	20 days
15°C (59°F)	3 hours	4 hours	10 days
20°C (68°F)	2 hours	3 hours	7 days
30°C (86°F)	1 hour	1.5 hours	5 days

Note: Adequate ventilation must be maintained during application and curing

SAFETY PRECAUTIONS

- See Safety Data Sheet and product label for complete safety and precaution requirements
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- EXPLANATION TO PRODUCT DATA SHEETS INFORMATION SHEET 1411

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

