

New Guard Coatings Group

A global reputation to protect.

You have acquired this data sheet from the New Guard Coatings Group.

All information listed is correct at the time of print.



uksales@newguardcoatings.com



+44 1937 586311

Global Head Office: New Guard Coatings Ltd, Sandbeck Way, Wetherby, Leeds, LS22 7DN



SIGMAWELD™ 165

DESCRIPTION

Two-component, moisture-curing, zinc (ethyl) silicate prefabrication primer

PRINCIPAL CHARACTERISTICS

- Suitable for automatic application on shot blasted steel plates
- Fast drying properties
- Good cutting and excellent welding properties, including MIG/MAG welding in various positions (either automatic or manual welding)
- Provides corrosion protection up to 9 months, when applied at a DFT of 13 µm (0.5 mil) (depending on exposure conditions and blasting profile)
- Can be used as a first coat in various paint systems
- Suitable for sea water immersion in combination with controlled cathodic protection systems
- Excellent thermal stability minimizes heat damage during hot work procedures
- No adherence of weldspatter at surrounding primed surface
- Approved by Lloyd's Register of Shipping for use as a prefabrication primer

COLOR AND GLOSS LEVEL

- Gray, reddish gray
- Flat

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.4 kg/l (11.7 lb/US gal)
Volume solids	30 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 428.0 g/kg max. 645.0 g/l (approx. 5.4 lb/US gal)
Recommended dry film thickness	13 µm (0.5 mils)
Theoretical spreading rate	23.1 m ² /l for 13 µm (962 ft ² /US gal for 0.5 mils)
Dry to touch	6 minutes
Overcoating Interval	Minimum: 3 days Maximum: 9 months
Shelf life	Binder: at least 12 months when stored cool and dry Paste: at least 12 months when stored cool and dry

Notes:

- See ADDITIONAL DATA - Curing time
- Longer overcoating intervals can be permitted when the primer is still in sound condition



SIGMAWELD™ 165

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; shot blast cleaned to ISO-Sa2½, blasting profile 30 – 75 µm (1.2 – 3 mils)
- On steel blasted to above profile, the recommended DFT of 13 µm (0.5 mil), corresponds to 15 µm (0.6 mil) as measured on a smooth test panel
- Minimum thickness for a closed film is 13 µm (0.5 mil) measured on a smooth test panel
- Dust quantity rating "1 for dust size class "3", "4" or "5", lower dust size classes to be removed if visible on the surface to be coated without magnification (ISO 8502-3:1992)

Substrate temperature and application conditions

- Substrate temperature during application should not exceed 50°C (122°F)
- Substrate temperature during application should be at least 3°C (5°F) above dew point
- Relative humidity during curing should be above 50% and below 85%

SYSTEM SPECIFICATION

- PREFABRICATION PRIMERS – SYSTEM SHEET 3015

SECONDARY SURFACE PREPARATION

- During storage and construction, contamination of the prefabrication primer should be limited
- After fabrication, surface defects should be treated according to the scheme hereafter
- Where two possible surface treatments are indicated, the choice of treatment is dependent on the location and on the system to be applied (see SYSTEM SHEETS)
- The preferred pre-treatment for optimal results is shown; other possibilities are indicated in brackets

SIGMAWELD™ 165

Secondary surface preparation		
Area	Immersed exposure conditions	Atmospheric exposure conditions
Contamination	To be removed	to be removed
Weldseams	ISO 8501-3 grade P2 and cleanliness ISO Sa 2 ½ (SPSS-Pt3)	SPSS-Pt2
Burned	ISO 8501-3 grade P2 and cleanliness ISO Sa 2 ½ (SPSS-Pt3)	SPSS-Ss (SPSS-Pt2)
Damaged corroded	ISO 8501-3 grade P2 and cleanliness ISO Sa 2 ½ (SPSS-Pt3)	SPSS-Ss (SPSS-Pt2)
White rust	ISO 8501-3 grade P2 and cleanliness ISO Sa 2 ½ (SPSS-Pt3)	SPSS-ID Pt1 (SCAP)

Notes:

- Cleaning by silicon carbide impregnated abrasive pad
- Dust quantity rating "1" for dust size class "3", "4" or "5", lower dust size classes to be removed if visible on the surface to be coated without magnification (ISO 8502-3)
- The back of welded plate may show discoloration (especially on plate where fillets have been welded on, this is not to be confused with burned areas and does not require special treatment
- Burned through areas may be present (this happens especially when welding thin steel) and these should then be treated as per 'burned areas' above

INSTRUCTIONS FOR USE

Mixing ratio by volume: binder to paste 55:45

- The temperature of the mixture of binder and paste should preferably be above 15°C (59°F)
- Stir the paste thoroughly before adding the binder
- Gradually add one-third of the binder to the pigment paste
- Stir thoroughly until homogeneous
- Add remaining binder and continue stirring until the mixture is homogeneous
- Strain the mixture through a 30–60 mesh screen
- Mixed paint is ready for use
- Some addition of thinner (THINNER 90-53) might be necessary depending on routing, line speed and steel temperature
- Agitate continuously during application

Pot life

24 hours at 20°C (68°F)



SIGMAWELD™ 165

Air spray

Recommended thinner

THINNER 90-53

Volume of thinner

0 - 35%, depending on required thickness and application conditions

Nozzle orifice

1.0 - 1.5 mm (approx. 0.040 - 0.060 in)

Nozzle pressure

0.3 MPa (approx. 3 Bar; 44 p.s.i.)

Airless spray

Recommended thinner

THINNER 90-53

Volume of thinner

0 - 35%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.48 - 0.64 mm (0.019 - 0.025 in)

Nozzle pressure

8.0 - 12.0 MPa (approx. 80 - 120 bar; 1161 - 1741 p.s.i.)

Note: Depending on exact application conditions a different thinner may be required to ensure optimal application properties. Consult the PPG Protective & Marine Coatings representative in your area when required.

Cleaning solvent

THINNER 90-53

ADDITIONAL DATA

Curing time for DFT up to 13 µm (0.5 mil)	
Substrate temperature	Dry to touch
20°C (68°F)	6 minutes
40°C (104°F)	3 minutes

SIGMAWELD™ 165

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490
• SPECIFICATION FOR MINERAL ABRASIVES	INFORMATION SHEET	1491
• RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE	INFORMATION SHEET	1650

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

