



# New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND



**PROTECTIVE  
&  
MARINE  
COATINGS**

**Resuprime MVT  
PRODUCT TECHNICAL DATA**

**PRODUCT DESCRIPTION**

Resuprime MVT is a two-component epoxy resin primer that is tolerant of residual moisture in concrete floors. This enables earlier access onto new concrete substrates for the application of screeds, coatings and other floor coverings including carpets, tiles, vinyl and wood. Resuprime MVT is available as a standard Clear or as Stirling Grey and is also used for existing concrete slabs where there is no damp-proof membrane or where a degree of moisture tolerance is required for a resin floor system being installed.

**ADVANTAGES**

- Ease of application
- Application onto substrates with Hygrometer readings up to 97% ERH
- Low odour
- Excellent adhesion
- Solvent free

**RECOMMENDED USE**

- “Green” concrete
- Concrete substrates with no DPM
- Polymer screeds
- Cementitious underlayments

**PRODUCT DATA**

<b>Volume Solids:</b>	~100%	<b>Application at 20°C</b>	
<b>VOC:</b>	85 g/l calculated per full mixed unit	<b>Recoating Intervals:</b>	6-8 hours or once surface has lost tackiness
<b>Colours:</b>	Clear or Stirling	<b>Light Traffic:</b>	18 – 24 hours
<b>Finish:</b>	Smooth gloss	<b>Full Traffic:</b>	48 – 72 hours
<b>Flash Point:</b>	N/A	<b>Full Chemical Cure</b>	7 days
<b>Cleanser/Thinner:</b>	N/A	<b>Pot Life:</b>	25 – 30 minutes from mixing, based on 5 kg pack size
<b>Pack Size:</b>	5 kg and 15 kg (MVT Clear) 6.7 kg and 20 kg (MVT Stirling)	<i>The pot life may be shorter for larger pack sizes if the paint is not used within the pot life limit.</i>	
<b>Pack Weights:</b>	3.33 kg base/1.67 kg hardener (5 kg) 5.00 kg Stirling base/1.67 kg hardener (6.7 kg) 9.99 kg base/5.01 kg hardener (15 kg) 15.00 kg Stirling base/5.01 kg hardener (20 kg)	<b>Note:</b> All mixed paint must be used within the pot life time limit, if the paint is left in the container after mixing and not used, it may release hazardous fumes due to exothermic reaction.	
<b>Mixing Ratio:</b>	2 parts base to 1 part hardener by weight only (Clear) 3 parts base to 1 part hardener by weight only (Stirling)	<b>Coverage Rate:</b>	5 kg will cover 23 m <sup>2</sup> @ 200 µm (Theoretical) WFT
<b>Mixed Density:</b>	Approximately 1.08 g/cm <sup>3</sup> (Clear) Approximately 1.25 g/cm <sup>3</sup> (Stirling)	<i>Coverage rate is calculated based on a sealed and smooth surface and may vary based on the substrate roughness and other conditions.</i>	
<b>Shelf Life:</b>	36 months (Base and Hardener)	<b>System Thickness: (Recommended)</b>	200 – 250 µm
<b>Storage:</b>	Keep out of direct sunlight. Store in a dry place, between 15°C – 30°C	<i>The suggested thickness range is calculated based on average volume solid as a general recommendation for the specified condition and for each application may vary.</i>	
		<b>Recommended Application Methods:</b>	Brush, roller or squeegee



## Resuprime MVT

### SURFACE PREPARATION

**New Concrete Floors:** New concrete must be clean, sound, dry, fully cured and surface laitance removed by vacuum enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm<sup>2</sup> is required.

**Existing Concrete Floors:** Remove all dirt, oil, grease, old paint or any other surface contaminants by vacuum enclosed shot blasting, scarifying or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing and making sure all residue of detergent is washed and removed by rinsing with clean water. Local repairs should be carried out using **Resuscreed PA**.

**Existing Floors (previously coated):** All previous coatings and loose floor paints must be removed by mechanical preparation as described in the above section and primed as specified. If the old resin flooring cannot be removed then please consult with our technical team for advice on intercoat adhesion and suitability, as it may not be compatible with the existing floor coating. Where **Resuprime MVT** is applied to masonry/concrete surfaces, care must be taken to ensure that surface preparation is thorough but does not disfigure the surface.

#### PRIMING

Where the Relative Humidity of a substrate exceeds 85% ERH **Resuprime MVT** should be specified and selected on the basis of hygrometer readings in accordance with BS 8203:2017. The number of coats to be applied is chosen in accordance with the following table:

ERH%	Required Coating Thickness
75-85	1 coat of Resuprime MVT at 200 µm per coat
85-92	2 coats of Resuprime MVT at 200 µm per coat
92-97	3 coats of Resuprime MVT at 200 µm per coat

#### MIXING

Mix the entire contents of **Resuprime Base** with **Resuprime MVT Hardener**. If a separate mixing bucket is being used mix thoroughly ensuring all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately two to three minutes until the two components are fully combined.

#### APPLICATION

The mixed unit should be applied immediately by roller, brush or squeegee with a consistent procedure. Floor areas should be cross-rolled to ensure even application and to minimise roller marks.

The ambient temperatures of the areas should not be allowed to fall below 15°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature must be above 10°C. Where possible it is recommended that the application area is heated to a minimum temperature of 15°C ideally to allow the ambient and substrate temperature to stabilise prior to the installation.

See *Sherwin-Williams System Sheets for recommended floor systems*.

#### WARRANTY

*Any person or company using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk, and Sherwin-Williams can accept no liability for the performance of the product, or for any loss or damage arising out of such use.*

*The information detailed in this datasheet is liable to modification from time to time in the light of experience and normal product development, and before using, customers are advised to check with Sherwin-Williams, quoting the reference number, to ensure that they possess the latest issue.*

#### TECHNICAL INFORMATION

The following figures are obtained from laboratory tests and our experience with this product.

<b>Category Guide:</b>	FerFA Category 2
<b>Bond Strength:</b>	>3 N/mm <sup>2</sup> (Substrate failure)
<b>Temperature Resistance:</b>	Tolerant of temperatures up to 60°C

#### DISCLAIMER

*The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.*

### HEALTH AND SAFETY

*Consult Product Health and Safety Datasheet for information on safe storage, handling and application of this product.*

Sherwin-Williams Protective & Marine Coatings, Tower Works, Kestor Street, Bolton, Lancashire BL2 2AL United Kingdom

T: 01204 521 771 E: [sales.uk@sherwin.com](mailto:sales.uk@sherwin.com) [www.resinflooring.sherwin.eu](http://www.resinflooring.sherwin.eu)

Registered in England 1659941 VAT GB 373 485624

[www.sherwin-williams.com/protectiveEMEA](http://www.sherwin-williams.com/protectiveEMEA)

*This datasheet is specifically subject to the disclaimer which can be found at: <http://protectiveemea.sherwin-williams.com/Home/Disclaimer>*