



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

Water based concrete curing compound

Uses

- As a spray applied membrane to retain moisture in concrete for effective curing
- Suitable for all general concreting applications and of particular benefit for large area concrete surfaces, such as airport runways, roads and bridgeworks

Advantages

- Improved curing of concrete enhances cement hydration and provides a more durable concrete
- Control of moisture loss improves surface quality, reducing permeability, producing a hard wearing, dust-free surface and minimising potential for surface cracking and shrinkage
- Fugitive colour provides visual guide during application
- Water based, therefore, non-flammable
- Spray application reduces labour costs and eliminates the need for alternative curing systems

Standards compliance

Concure WB gives 75% or greater curing efficiency when tested to BS 7542 and complies with ASTM C309 and AASHTO M148 as Type 1.

Description

Concure WB is a water based concrete curing compound based on a low viscosity wax emulsion. It is supplied as a white emulsion which forms a clear film on drying.

When first applied to a fresh cementitious surface the emulsion breaks to form a continuous, non-penetrating white coating. This dries to form a continuous clear film which provides a barrier to moisture loss, ensuring more efficient cement hydration, improved durability and reduced shrinkage.

Application instructions

Minimum application temperature: 5°C

Concure WB should be spray applied to the surface of fresh concrete. Application should begin immediately the concrete is free from surface water. Do not apply if bleed water is forming or present on the concrete surface.

The spray nozzle should be held approximately 450 mm from the concrete surface and passed back and forth to ensure complete coverage. The fugitive white colour during application provides a guide to the area covered. Pump pressure should be maintained to give an even, fine spray.

After spraying, no further application of water is necessary to ensure continued curing. The concrete surface should not be disturbed until it has sufficient strength to bear surface loads. The applied film should not be walked on before it is fully dry and care should be taken to ensure that the film is not broken.

Concure WB may also be applied to the surface of newly hardened concrete immediately after demoulding. In such cases the concrete surface must be damp and not dry. Dry surfaces may prevent correct film formation and cause absorption of the Concure WB which may lead to staining and difficulty in later removal.

Coverage rate

The recommended coverage rate is between 3.5 and 5.0 m²/litre (0.200 to 0.285 litres/m²). Coverage rates outside this recommended range may be used if necessary and suitable to meet specific requirements. Contact the Fosroc Customer Service Department for advice in such cases.

Equipment

Spray equipment producing a fine mist without damaging the emulsion may be used for Concure WB, such as knapsack or motorised sprayers. The suitability of equipment should be ensured by an application trial.

Equipment cleaning

Spray equipment should be cleaned immediately after use by flushing through with water. If spray nozzles become blocked with wax particles these may be easily cleared with white spirit.

Overcoating and removal

Concure WB must be removed from a concrete surface before application of a subsequent coating to ensure a good bond of the coating material to the concrete. Concure WB will be slowly removed by physical abrasion in normal trafficking and exposure. To ensure complete removal use high pressure steam, water jet or light sand blasting.

Limitations

Concure WB should not be continuously re-circulated in high shear pumps in concrete train or similar applications as this may cause a breakdown of the emulsion before spraying. If continuous recirculation is necessary, the sprayer should be fitted with a low shear diaphragm pump.

In extreme drying conditions additional curing using polythene or wet muslin may be required.

Estimating

Supply

Concure WB is supplied in 200 litre and 20 litre drums.

Storage

Concure WB has a minimum shelf life of 12 months provided the temperature is kept within the range of 4°C to 35°C. Freezing and prolonged exposure to heat or direct sunlight should be avoided. Should the temperature of the product fall outside this range then the Fosroc Customer Service Department should be contacted for advice.

Containers should be kept sealed and airtight to prevent loss of moisture by evaporation.

Fosroc® Concure WB

Precautions

Health and safety

For further information refer to appropriate Product Safety Data Sheet.

Fire

Concure WB is water based and non-flammable.

Fosroc and Concure are trademarks of
Fosroc International Limited



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

Fosroc Limited

Drayton Manor Business Park
Coleshill Road, Tamworth,
Staffordshire B78 3TL. UK

www.fosroc.com

telephone:
+44 (0) 1827 262222

fax:
+44 (0) 1827 262444

email:
uk@fosroc.com



Certificate number FM 610