



# New Guard Coatings Group

- A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

# SIGMA SAILADVANCE™ GX

## DESCRIPTION

Low friction, self lubricating, linear self polishing high activity performance antifouling based on hydrolysable binder composition

## PRINCIPAL CHARACTERISTICS

- Designed for all vessel types and speeds and particularly effective for slow steaming because of its engineered oils binder composition
- Evolves in a linear polishing and consistent biocide release for predictable performance up to 90 months
- Designed for broad range of vessel operational profiles
- Constant surface activity, limited leach layer build-up
- Low friction properties from lubricating engineered oils suppressing turbulent flow
- Extended idle days through the release effect of engineered oils creating a slippery surface
- High volume solids for efficient application
- Suitable for application at New Build and Dry Dockings
- Based on PPG technology

## COLOR AND GLOSS LEVEL

- Redbrown, brown
- Flat

## BASIC DATA AT 20°C (68°F)

Data for product	
Number of components	One
Mass density	1.7 kg/l (14.2 lb/US gal)
Volume solids	59 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 227.0 g/kg max. 398.0 g/l (approx. 3.3 lb/US gal)
Recommended dry film thickness	75 - 165 µm (3.0 - 6.5 mils) depending on system
Theoretical spreading rate	3.6 m <sup>2</sup> /l for 165 µm (146 ft <sup>2</sup> /US gal for 6.5 mils)
Dry to touch	2 hours
Overcoating Interval	Minimum: 6 hours
Refloating time	Minimum: 12 hours
Shelf life	At least 12 months when stored cool and dry

### Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals



# SIGMA SAILADVANCE™ GX

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Substrate conditions

- Previous coat must be sound, dry and free from any contamination
  - Suitable high performance anticorrosive tiecoats
- 

### Substrate temperature and application conditions

- Substrate temperature during application should be at least 3°C (5°F) above dew point
  - Relative humidity during application and curing should not exceed 85%
- 

## INSTRUCTIONS FOR USE

- Stir well before use
  - The temperature of the paint should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
  - Adding too much thinner results in reduced sag resistance
- 

### Airless spray

#### **Recommended thinner**

THINNER 21-06

#### **Volume of thinner**

0 - 3%, depending on required thickness and application conditions

#### **Nozzle orifice**

Approx. 0.53 - 0.69 mm (0.021 - 0.027 in)

#### **Nozzle pressure**

12.0 - 15.0 MPa (approx. 120 - 150 bar; 1741 - 2176 p.s.i.)

---

### Brush/roller

- Only for touch-up and spot repair

#### **Recommended thinner**

THINNER 21-06

#### **Volume of thinner**

0 - 3%

---

### Cleaning solvent

THINNER 21-06

---



# SIGMA SAILADVANCE™ GX

## ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
75 µm (3.0 mils)	7.9 m <sup>2</sup> /l (315 ft <sup>2</sup> /US gal)
100 µm (4.0 mils)	5.9 m <sup>2</sup> /l (237 ft <sup>2</sup> /US gal)
150 µm (6.0 mils)	3.9 m <sup>2</sup> /l (158 ft <sup>2</sup> /US gal)
165 µm (6.5 mils)	3.6 m <sup>2</sup> /l (146 ft <sup>2</sup> /US gal)

Overcoating interval for DFT up to 165 µm (6.5 mils)							
Overcoating with...	Interval	-5°C (23°F)	0°C (32°F)	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)
itself	Minimum	24 hours	18 hours	12 hours	10 hours	6 hours	4 hours
	Refloating - Minimum	36 hours	30 hours	24 hours	16 hours	12 hours	9 hours

Notes:

- Longer drying times may be necessary at higher DFT and under unfavorable atmospheric conditions
- Above table is a fair indication for normal application conditions. Please contact your PPG representative for data at much lower and higher DFT conditions

## SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

## REFERENCES

- |  |                   |      |
|--|-------------------|------|
| • EXPLANATION TO PRODUCT DATA SHEETS   | INFORMATION SHEET | 1411 |
| • SAFETY INDICATIONS   | INFORMATION SHEET | 1430 |
| • SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD | INFORMATION SHEET | 1431 |

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.



# SIGMA SAILADVANCE™ GX

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

Depending on specific country of application the following versions are available:

Article code	Color	Reference
371293	redbrown	2008002200
371294	brown	2000002200

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

