

# New Guard Coatings Group

A global reputation to protect.

You have acquired this data sheet from the New Guard Coatings Group.

All information listed is correct at the time of print.



[uksales@newguardcoatings.com](mailto:uksales@newguardcoatings.com)



+44 1937 586311

Global Head Office: New Guard Coatings Ltd, Sandbeck Way, Wetherby, Leeds, LS22 7DN



## Pure Epoxy

**PRODUCT DESCRIPTION** A two pack epoxy abrasion resistant coating, containing micaceous iron oxide, which can be overcoated after extended periods.

**INTENDED USES** As a general purpose primer for all non-permanently immersed areas.  
For use at Newbuilding.

**PRODUCT INFORMATION**

<b>Colour</b>	EPA001-MIO Dark Grey, EPA007-MIO Light Grey
<b>Finish/Sheen</b>	Not applicable
<b>Part B (Curing Agent)</b>	EPA740
<b>Volume Solids</b>	65% ±2% (ISO 3233:1998)
<b>Mix Ratio</b>	5.67 volume(s) Part A to 1 volume(s) Part B
<b>Typical Film Thickness</b>	125 microns dry (192 microns wet)
<b>Theoretical Coverage</b>	5.2 m <sup>2</sup> /litre at 125 microns dft, allow appropriate loss factors
<b>Method of Application</b>	Airless Spray, Roller, Brush
<b>Flash Point (Typical)</b>	Part A 23°C; Part B 23°C; Mixed 25°C
<b>Induction Period</b>	30 minutes at temperatures below 25°C

Drying Information	0°C	5°C	25°C	35°C
Touch Dry [ISO 9117/3:2010]	12 hrs	3 hrs	2 hrs	60 mins
Hard Dry [ISO 9117-1:2009]	36 hrs	36 hrs	12 hrs	8 hrs
Pot Life	13 hrs	12 hrs	6 hrs	2 hrs

Overcoating Data - see limitations	Substrate Temperature							
	0°C		5°C		25°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Intergard 269	26 hrs	ext	20 hrs	ext	16 hrs	ext	14 hrs	ext
Intergard 400	24 hrs	ext	16 hrs	ext	12 hrs	ext	8 hrs	ext
Intergard 410	24 hrs	ext	20 hrs	ext	16 hrs	ext	14 hrs	ext
Intergard 415	-	-	24 hrs	ext	16 hrs	ext	12 hrs	ext
Intergard 740	-	-	16 hrs	ext	12 hrs	ext	8 hrs	ext
Interthane 990	-	-	48 hrs	7 days	16 hrs	5 days	12 hrs	3 days
Intertherm 891	-	-	16 hrs	7 days	12 hrs	5 days	8 hrs	3 days

**Note** For overcoating Intergard 400 with Intergard 410, Intergard 415 and Intergard 740 see Special Note in Surface Preparation section.

**REGULATORY DATA**

<b>VOC</b>	307 g/lit as supplied (EPA Method 24) 221 g/kg of liquid paint as supplied. EU Solvent Emissions Directive (Council Directive 1999/13/EC) 325 g/lit Chinese National Standard GB23985
------------	---

**Note:** VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

## Pure Epoxy

### CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Food Contact - Carriage of Grain (NOHA)
- Fire Resistance - Surface Spread of Flame (Exova Warringtonfire)
- Fire Resistance - Smoke & Toxicity (Exova Warringtonfire)
- Fire Resistance - Marine Equipment Directive compliant

Consult your International Paint representative for details.

---

### SYSTEMS AND COMPATIBILITY

Consult your International Paint representative for the system best suited for the surfaces to be protected.

---

### SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

#### NEWBUILDING

Where necessary, remove weld spatter and smooth weld seams and sharp edges.

Weld seams and areas of shop primer damage or breakdown should be blast cleaned to Sa2½ (ISO 8501-1:2007) or power tooled to Pt3 (JSRA SPSS:1984).

Intact shop primers must be clean, dry and free from soluble salts and any other surface contaminants.

If the shop primer shows extensive or widely scattered breakdown, overall sweep blasting may be necessary.

Consult your International Paint representative for specific recommendations.

#### SPECIAL NOTE

When overcoating with Intergard 410, Intergard 415 and Intergard 740 the anticipated level of intercoat adhesion can only be achieved in "extended" overcoating situations when:

a) the aged coating has the "extended" surface characteristics required for long term overcoatability. For example, an over applied epoxy MIO may not have its usual "textured" surface and will no longer be overcoatable after ageing unless it is abraded.

b) the coating to be overcoated is intact, tightly adherent, clean, dry and free of all contaminants.

c) coatings with a glossy surface are treated by light surface abrasion, sweep blasting or other suitable processes which do not cut through or detract from the performance of the underlying coating.

Consult your International Paint representative for specific recommendations.

#### NOTE

**For use in Marine situations in North America, the following surface preparation standards can be used: SSPC-SP10 in place of Sa2½ (ISO 8501-1:2007)**

## Pure Epoxy

### APPLICATION

<b>Mixing</b>	Material is supplied in 2 containers as a unit. Always mix a complete unit in the proportions supplied. (1) Agitate Base (Part A) with a power agitator. (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.
<b>Thinner</b>	International GTA220. Thinning is not normally required. Consult the local representative for advice during application in extreme conditions. Do not thin more than allowed by local environmental legislation.
<b>Airless Spray</b>	Recommended Tip Range 0.46-0.58 mm (18-23 thou) Total output fluid pressure at spray tip not less than 176 kg/cm <sup>2</sup> (2500 p.s.i.)
<b>Conventional Spray</b>	Application by conventional spray is not recommended.
<b>Brush</b>	Application by brush is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
<b>Roller</b>	Application by roller is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
<b>Cleaner</b>	International GTA822
<b>Work Stoppages and Cleanup</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA822. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units. Clean all equipment immediately after use with International GTA822. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature, relative humidity and elapsed time, including any delays. Do not exceed pot life limitations. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.
<b>Welding</b>	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

### SAFETY

**All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.**

**Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.**

#### **EMERGENCY CONTACT NUMBERS:**

**USA/Canada - Medical Advisory Number 1-800-854-6813**

**Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191**

**China – Contact (86) 532 83889090**

**R.O.W. - Contact Regional Office**

## Pure Epoxy

### LIMITATIONS

This product will not cure adequately below 0°C. For maximum performance ambient curing temperature should be above 5°C.

Optimum performance is achieved when Intergard 400 is applied over blasted steel.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. Apply in good weather. Temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

In the overcoating data section 'ext' = extended overcoating period. Please refer to our Marine Painting Guide - Definitions and Abbreviations available on our website.

UNIT SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	20 lt	17 lt	20 lt	3 lt	5 lt

*For availability of other unit sizes consult International Paint*

UNIT SHIPPING WEIGHT (TYPICAL)	Unit Size	Unit Weight
	20 lt	36.04 Kg

STORAGE	Shelf Life	12 months minimum at 25°C. Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.
---------	------------	---

**WORLDWIDE AVAILABILITY** Consult International Paint.

### IMPORTANT NOTE

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2016

[www.international-marine.com](http://www.international-marine.com)