



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

Guard HTB - High Temperature Black



Technical Data Sheet

Product Description:

A single pack, heat resistant, protective and decorative black coating for use at temperatures up to 600°C.

Typical Uses:

A single component paint which is ideal for interior use onto suitably prepared steel and metal. Temperature resistant up to 600°C.

Practical Information:

Colours	Black
Pack Size	5 litre
Gloss Level	Matt, Sheen
Resin Type	PVB Modified Alkyd
Components	Single Component
Generic Type	Solvent-based

Technical Information:

Theoretical Spreading Rate (approx)	21m ² per litre based on 15µm dft
Volume Solids (approx)	35%
Dry Film Thickness (DFT)	15-17µm
Wet Film Thickness (WFT)	50µm
Flash Point	23-32°C
VOC Content	600gms/litre
Temperature Resistance	600°C

Surface Preparation:

Ensure surfaces are clean, dry and free from grease and other contamination before coating. Thoroughly degrease and where applicable, abrade to remove rust and promote good adhesion of the coating. For optimum corrosion protection, mild steel should be blast cleaned to Sa2.5. Complex structures may be more effectively cleaned by HPWJ (high pressure water jetting).

Mixing:

Mix Ratio: Not applicable.
Mixing Instructions: This material is a one-component coating and should always be mixed thoroughly with an agitator before application.
Pot Life: Not applicable.

Application Methods:

Brush	Yes	Small areas only
Roller	Yes	
Conventional Spray	Yes	Thinner should not be required - maximum 5%
Airless Spray	Yes	Not optimised
Air Assisted Airless Spray	No	

For further information and guidance on application, please speak with our technical team.

Solvents:

Thinning: Guard Solvent A
Cleaning: Guard Solvent A

Drying and Curing Time:

Touch Dry	15-20 minutes
Hard Dry	4 hours
Full Cure	Will occur after coating has been raised to a service temperature of at least 220°C for 20-30 minutes
Recoatible	Not recommended - small areas only

Drying times are based on temperatures of 20°C, lower temperatures will increase drying times. Please speak with our technical team before elevating temperatures or attempting to force cure any of our products unless already stated. Shop conditions such as having good airflow will optimise curing.

Compatibility:

Should be applied directly to suitably prepared steel. Not suitable to be topcoated.

Cleaning Information:

Once painting has been completed, clean all equipment with abovementioned cleaning solvent. Spray equipment should be appropriately flushed through for 3-5 minutes (returning unused paint to the tin, unless thinned which should be stored in a separate tin) before replacing any used solvent with clean solvent to leave in the pump, gun and lines.

Storage & Shelf-Life:

Unopened tins should be stored in a cool dry place between the temperatures of 5° and 25°C – better storage conditions will likely extend the shelf-life of the material. Always stir thoroughly before re-use.

Product has a shelf life of 6 to 8 months as standard from the date of manufacture. Once opened tins should have the lid fitted tightly when not in use. Please speak with us before using material which is past it's standard shelf-life as certain materials may need re-certifying before use.

Safety Precautions:

To avoid the risk of spillage always store and transport in an upright secure position. Materials are hazardous and can also be flammable therefore appropriate precautionary measures must be taken including the use of gloves, glasses and recommended P.P.E in accordance with the material safety data sheets (MSDS).

Review

Document Reference: A1HTB1.1
Version Date: October 2021
Stock Code: GHTB

Important Notes & Disclaimer:

The above information should be used as a guide only and is not a guarantee or warranty. The New Guard Coatings Group and our supply / manufacturing partners have provided this information in good faith and to the best of our knowledge correct at the time of print. 'Guard' is a brand owned by New Guard Holdings Ltd.

No liability will be accepted for incorrect colours or any other failure by the customer to check before use. This does not affect your statutory rights.

www.newguardcoatings.com