



# New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND



# Guard SCF - Single Coat Finish

## Technical Data Sheet

### Product Description:

Single pack, one coat product for suitably prepared steel. Fast drying for optimum throughput.

### Typical Uses:

As a high quality single coat finish for application onto mild steel and other suitably prepared surfaces. Ideal for applications which require a fast turnaround, such as manufacturers of modular components and other OEM companies.

### Practical Information:

Colours	Full tintable colour range. All RAL & BS4800 colours and specials on request
Pack Size	5 litre, 20 litre (Nominal Volumes)
Gloss Level	Matt, Satin, Gloss
Resin Type	Alkyd
Components	Single Component
Generic Type	Solvent-based

### Technical Information:

Theoretical Spreading Rate (approx)	6m <sup>2</sup> per litre based on 60µm dft
Volume Solids (approx)	60%
Dry Film Thickness (DFT)	60-90µm
Wet Film Thickness (WFT)	100-150µm
Flash Point	24°C
VOC Content	505gms/litre
Temperature Resistance	80°C

### Surface Preparation:

Ensure surfaces are clean, dry and free from grease and other contamination before coating. Thoroughly degrease and where applicable, abrade to remove rust and promote good adhesion of the coating. For optimum corrosion protection, mild steel should be blast cleaned to Sa2.5. Complex structures may be more effectively cleaned by HPWJ (high pressure water jetting).

For the best corrosion protection we recommend stripe coating all edges and hard to reach areas with this product first, before application of a full coat.

### Mixing:

<b>Mix Ratio:</b>	Not applicable.
<b>Mixing Instructions:</b>	This material is a one-component coating and should always be mixed thoroughly with an agitator before application.
<b>Pot Life:</b>	Not applicable.

## Application Methods:

Brush	No	Not optimised - small areas only, including stripe coating
Roller	No	
Conventional Spray	Yes	Thin up to 10% - added as approx. 3-5% each time
Airless Spray	Yes	
Air Assisted Airless Spray	Yes	Optimised

For further information and guidance on application, please speak with our technical team.

## Solvents:

**Thinning:** Guard Solvent A  
**Cleaning:** Guard Solvent A

## Drying and Curing Time:

Touch Dry	2 hours
Hard Dry	24 hours
Full Cure	24 hours
Recoatable	Unlimited

Drying times are based on temperatures of 20°C, lower temperatures will increase drying times. Please speak with our technical team before elevating temperatures or attempting to force cure any of our products unless already stated. Shop conditions such as having good airflow will optimise curing.

## Compatibility:

Designed as a 'OneCoat' primer/finish, though is compatible with most single component primers, such as Guard GIP or Guard EP. Likewise can be overcoated with alkyd topcoats such as Guard FEB or Guard FES.

## Cleaning Information:

Once painting has been completed, clean all equipment with abovementioned cleaning solvent. Spray equipment should be appropriately flushed through for 3-5 minutes (returning unused paint to the tin, unless thinned which should be stored in a separate tin) before replacing any used solvent with clean solvent to leave in the pump, gun and lines.

## Storage & Shelf-Life:

Unopened tins should be stored in a cool dry place between the temperatures of 5° and 25°C – better storage conditions will likely extend the shelf-life of the material. Always stir thoroughly before re-use.

Product has a shelf life of 12 months as standard from the date of manufacture. Once opened tins should have the lid fitted tightly when not in use. Please speak with us before using material which is past it's standard shelf-life as certain materials may need re-certifying before use.

## Safety Precautions:

To avoid the risk of spillage always store and transport in an upright secure position. Materials are hazardous and can also be flammable therefore appropriate precautionary measures must be taken including the use of gloves, glasses and recommended P.P.E in accordance with the material safety data sheets (MSDS).

## Review

**Document Reference:** A1SCF1.1  
**Version Date:** October 2021  
**Stock Code:** GSCF

## Important Notes & Disclaimer:

The above information should be used as a guide only and is not a guarantee or warranty. The New Guard Coatings Group and our supply / manufacturing partners have provided this information in good faith and to the best of our knowledge correct at the time of print. 'Guard' is a brand owned by New Guard Holdings Ltd.

No liability will be accepted for incorrect colours or any other failure by the customer to check before use. This does not affect your statutory rights.

[www.newguardcoatings.com](http://www.newguardcoatings.com)