



☐ A global reputation to protect.

You have acquired this data sheet from the New Guard Coatings Group.

All information listed is correct at the time of print.



uksales@newguardcoatings.com



+44 1937 586311

Global Head Office: New Guard Coatings Ltd, Sandbeck Way, Wetherby, Leeds, LS22 7DN



Ace Coatings South



HYDROBARP FONDO CARE



Product Description	Single component transparent water based undercoat
Properties	Acrylic nature High covering power Excellent transparency Quick drying product Good manual sanding after 4-6 hours
Recommended use	Product to use for varnishing woodwork and indoor furniture
Certificados	Hydrobarp.Fondo.y.Acabado.UV.pdf , 0804051-04.pdf , Certificado.de.Producto.Simbolo.de.Calidad.AIDIMA



Technical Characteristics

	Norma	Value
Solids by weight (%)	UNE EN ISO 3251	38+-2%
Viscosity (Ford cup 4)	UNE EN ISO 2431	63+-5" F.4 20 G.C.
Density (Kg/L)	UNE EN ISO 2811-1	1.04+/-0.020
VOCs (%)	UNE EN ISO 11890	5.095%
VOCs (gr./lt)	UNE EN ISO 11890	52.988

Mixing Characteristics

Solvent	Water
Percentage dilution	5-10%

Application Characteristics

Application System	Aerographic, airmix and airless
Recommended quantity of product	100-120 gr/m ²
Temperature of Application	>15
Ambient Humidity	Less than 70%
Touch-dry	40 a 60 minutes (depending on thickness and temperature)
Can be handled	90 a 100 minutes (depending on thickness and temperature)
Surface sanding	4 - 6 hours, depending on thickness applied and ambient conditions
Repainted	16-24 hours

Remarks re application process

If you wish to seal the wood pores, you must sand the first undercoat before applying a second coat
The moisture content of the wood to be treated must not exceed 15%
If you wish to shorten drying time, you can force-dry with hot air or use infrared or microwave driers.

Remarks

Shake contents of containers before use.
Clean utensils with water immediately after use.
Do not store at below 5°C
For toxicological standards, consult FICHA DE SEGURIDAD.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 28-12-2010 This sheet replaces all previous versions.