



New GuardCoatingsGroup

☐ Aglobalreputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

Epoxy

PRODUCT DESCRIPTION

Atwo component, solvent free, heavy duty epoxy tank lining.

INTENDED USES

For application to steel tank internals to provide corrosion resistance to a range of products including crude oil, white oils and potable water.

Suitable for application over concrete for lining and secondary containment purposes.

PRACTICAL INFORMATION FOR INTERLINE 975

Colour	Cream, White																												
Gloss Level	Not applicable																												
Volume Solids	100%																												
Typical Thickness	300-600 microns (12-24 mils) dry equivalent to 300-600 microns (12-24 mils) wet 400-1000 microns (16-40 mils) for use as a single coat on tank floors. Thickness is dependent upon application method and specification.																												
Theoretical Coverage	2.50 m ² /litre at 400 microns d.f.t and stated volume solids 100 sq.ft/US gallon at 16 mils d.f.t and stated volume solids																												
Practical Coverage	Allow appropriate loss factors.																												
Method of Application	Airless Spray, Brush, Roller																												
Drying Time	Overcoating interval with self <table> <tr> <th>Temperature</th><th>Touch Dry</th><th>Hard Dry</th><th>Minimum</th><th>Maximum</th></tr> <tr> <td>10°C (50°F)</td><td>15 hours</td><td>36 hours</td><td>36 hours</td><td>28 days¹</td></tr> <tr> <td>15°C (59°F)</td><td>12 hours</td><td>24 hours</td><td>24 hours</td><td>28 days¹</td></tr> <tr> <td>25°C (77°F)</td><td>7 hours</td><td>16 hours</td><td>16 hours</td><td>14 days¹</td></tr> <tr> <td>40°C (104°F)</td><td>3 hours</td><td>6 hours</td><td>6 hours</td><td>14 days¹</td></tr> </table>				Temperature	Touch Dry	Hard Dry	Minimum	Maximum	10°C (50°F)	15 hours	36 hours	36 hours	28 days ¹	15°C (59°F)	12 hours	24 hours	24 hours	28 days ¹	25°C (77°F)	7 hours	16 hours	16 hours	14 days ¹	40°C (104°F)	3 hours	6 hours	6 hours	14 days ¹
Temperature	Touch Dry	Hard Dry	Minimum	Maximum																									
10°C (50°F)	15 hours	36 hours	36 hours	28 days ¹																									
15°C (59°F)	12 hours	24 hours	24 hours	28 days ¹																									
25°C (77°F)	7 hours	16 hours	16 hours	14 days ¹																									
40°C (104°F)	3 hours	6 hours	6 hours	14 days ¹																									

¹ The values quoted relate to use within an enclosed tank environment. For situations where UV exposure between coats is likely, maximum overcoating intervals will be shorter. Contact International Protective Coatings for more details.

REGULATORY DATA

Flash Point (Typical)	Part A >101°C (214°F); Part B >101°C (214°F); Mixed >101°C (214°F)		
Product Weight	1.33 kg/l (11.1 lb/gal)		
VOC	0.00 lb/gal (0 g/l)	USA - EPA Method 24	
	0g/kg	EU Solvent Emissions Directive (Council Directive 1999/13/EC)	

See Product Characteristics section for further details

Epoxy SURFACE PREPARATION

All surfaces to be coated should be clean and free from contamination. Prior to application all surfaces should be assessed and treated in accordance with ISO 8504:2000. Where necessary, remove weld spatter and smooth weld seams and sharp edges. Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Abrasive Blast Cleaning

This product must only be applied to surfaces prepared by abrasive blast cleaning to Sa2½ (ISO 8501-1:2007) or SSPC-SP10. A sharp angular surface profile of 75-100 microns (3-4 mils) is recommended. Interline 975 must be applied before oxidation of the steel occurs. If oxidation does occur the entire oxidised area should be reblasted to the standard specified above.

Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner.

Where local VOC regulations allow, surfaces may be primed with Interline 982 to 15-25 microns (0.5-1.0 mils) dry film thickness before oxidation occurs. Alternatively, the blast standard can be maintained by use of dehumidification.

Interline 982 can hold a blast for up to 28 days in the semi-protected environment of a tank interior. If moisture is present on the surface, oxidation will occur and reblasting will be required.

APPLICATION

Concrete Surfaces
Mixing
Refer to International Protective Coatings for specific recommendations and the details in International Protective Coatings Recommended Working Procedures for application of Tank Linings.

Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.

- (1) Agitate Base (Part A) with a power agitator.
- (2) Agitate Curing Agent (Part B) with a power agitator.
- (3) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.

Mix Ratio

2.2 part(s) : 1 part(s) by volume

Working Pot Life

10°C (50°F)	15°C (59°F)	25°C (77°F)	40°C (104°F)
90 minutes	80 minutes	60 minutes	30 minutes

Airless Spray

Recommended

Tip Range 0.53-0.66 mm (21-26 thou)
Total output fluid pressure at spray tip not less than 211 kg/cm² (3000 p.s.i.)

Air Spray (Pressure Pot)

Not recommended

Brush

Suitable - small areas only

Typically 150-200 microns (6.0-8.0 mils) can be achieved

Roller

Suitable - small areas only

Typically 150-200 microns (6.0-8.0 mils) can be achieved

Thinner

Not suitable - DO NOT THIN

Cleaner

International GTA853 (or International GTA415)

Work Stoppages

Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA853. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.

Clean Up

Clean all equipment immediately after use with International GTA853. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.

Epoxy PRODUCT CHARACTERISTICS

The detailed Interline 975 Application Guidelines should be consulted prior to use.

Exact specification for total dry film thickness and number of coats will be dependent upon service end use requirements. Consult International Protective Coatings for specific advice regarding tank lining applications.

Interline 975 is a solvent free high viscosity material and can be applied by standard airless spray equipment. Refer to Interline 975 Application Guidelines for detailed information. Apply by airless spray only. Application by other methods, e.g. brush or roller, may require more than one coat and is suggested for small areas only or initial stripe coating. Heavily pitted areas should be stripe coated by brush, to ensure good "wetting" of the surface.

Do not apply at steel temperatures below 10°C (50°F). Surface temperature must always be a minimum of 3°C (5°F) above dew point. The climatic conditions within the tank must be controlled as recommended in the Interline 975 Application Guidelines.

The relative humidity within the confines of the tank should be controlled using dehumidification equipment. Where such equipment is not available, a single coat application technique should be employed to avoid intercoat adhesion problems. Where multi-coat systems are to be used, optimum intercoat adhesion is best achieved by keeping the overcoating interval as short as possible.

Exposure to unacceptably low temperatures and/or high humidities during or immediately after application may result in incomplete cure and surface contamination that could jeopardise subsequent intercoat adhesion.

After the last coat has cured hard, the coating system dry film thickness should be measured using a suitable non-destructive magnetic gauge to verify the average total applied system thickness. The coating system should be free of all pinholes or other holidays and verified using a suitable method as recommended in the Interline 975 Application Guidelines. The cured film should be essentially free of runs, sags, drips, inclusions or other defects. All deficiencies and defects should be corrected. The repaired areas shall be retested and allowed to cure as specified before placing the finished lining into service. Consult International Protective Coatings Interline 975 Application Guidelines for detailed repair procedures.

Return to Service

The following minimum cure times are recommended for Interline 975 to achieve its full chemical resistance properties.

	<u>Cure Schedule</u>
	21 days
Temperature	14 days
7°C (45°F)	9 days
10°C (50°F)	7 days
15°C (59°F)	5 days
25°C (77°F)	4 days
35°C (95°F)	
40°C (104°F)	

Cure schedule refers to the minimum time at the specified substrate temperature prior to immersion in all chemicals as per the chemical resistance list. This does not take into consideration any specific curing requirements for third party approvals, such as for potable water use. For storage of cargoes above ambient temperatures, consult International Protective Coatings for further details.

In common with all epoxies Interline 975 will chalk and discolour on exterior exposure. However, these phenomenon are not detrimental to chemical resistance performance.

This product has the following specification approvals:

- BS6920:2000 for contact with cold and hot potable water.
- Norwegian National Institute of Public Health for Use in Potable Water Tanks on Offshore Installations.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances. Interline 975 can be applied directly to correctly prepared bare steel. However, it is suitable for application over the following primer:

Interline 982

Ceilmate 680M (to be used as a sealer for concrete application)

Interline 975 should only be topcoated with itself, and should never be overcoated with another product.

Consult International Protective Coatings to confirm that Interline 975 is suitable for contact with the product to be stored.

SYSTEMS COMPATIBILITY

Epoxy

ADDITIONAL
INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage
- Interline 975 Application Guidelines

Individual copies of these information sections are available upon request.

SAFETY
PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations. All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety and Environmental standards, regulations and legislation.

Proper ventilation must be provided during application and afterwards during curing (refer to product datasheets for typical curing times) to ensure safe limits and prevent fires and explosions. Forced extraction will be required in confined spaces. Ventilation and/or respiratory personal protective equipment (airfed hoods or appropriate cartridge masks) must be provided during application and curing. Take precautions to avoid skin and eye contact (overalls, gloves, goggles, masks, barrier cream, etc).

Before use, obtain, read and then follow the advice given on the Material Safety Data Sheets (Parts A and B if two-pack) and the Health and Safety section of the Coatings Applications Procedures for this product.

In the event that welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

The detailed safety measures are dependent on application methods and the work environment. If you do not fully understand these warnings and instructions or if you cannot strictly comply with them, do not use the product and consult International Protective Coatings.

Warning: This product contains liquid epoxies and modified polyamines and may cause skin sensitisation if not used correctly.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	4.5 US gal	3.17 US gal	5 US gal	1.33 US gal	2 US gal
	16 litre	11 litre	20 litre	5 litre	5 litre
For availability of other pack sizes, contact International Protective Coatings.					
SHIPPING WEIGHT (TYPICAL)	Unit Size		Part A		Part B
	4.5 US gal		43 lb		11.9 lb
	16 litre		17.93 kg		5.45 kg
STORAGE	Shelf Life	12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

Important Note

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 31/07/2017.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

www.international-pc.com