



New Guard Coatings Group

- A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

PRODUCT DATA

MURFILL FLEECE (non woven)

DESCRIPTION

Polyester fibres.

RECOMMENDED USES

Reinforcement of the first coat of the Murfill-Waterproofing system on flat surfaces.

TECHNICAL DATA (according to the data given by the manufacturer)

Composition		:	100% polyester fibres
Quality		:	Non woven
Weight		:	50 g/m ²
Thickness		:	0,2 mm
Traction force in N/5 cm	By warp	:	± 110
	By weft	:	± 100
GRAB elongation in %	By warp	:	± 32
	By weft	:	± 35
Resistance to	UV	:	Good - behind glass 7 to 10 years
	Temperature	:	Good – 160°C
	Acids	:	Good
	Alkali	:	Good
Thermal retraction at 40°C		:	No tests, according to manufacturer < 1%
Dimensions	Widths	:	16 cm en 100 cm
	Roll length	:	100 m
Tolerances	Width	:	Geen
	Length	:	- 0 m + 1 m

Rust-Oleum Netherlands B.V.
Blaak 1, 4704 RJ
P.O. Box 138, 4700 AG
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info@rust-oleum.eu
www.rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zeltem
Halen, Belgium
T +32 (0)13 480 200
F +32 (0)13 480 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S
11, Rue Jules Verne, B.P. 60039
95322 St-Lau-la-Forêt Cedex
France
T +33 (0)1 30 40 00 44
F +33 (0)1 30 40 99 60
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.
Rotterdam House
116 Quayside
Newcastle
NE1 3DY
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info@rust-oleum.eu
www.rust-oleum.eu