



# New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

## PRIMER 6000 WHITE

<b>Product characteristics</b>	Two component white acid solvent-based primer.
<b>Properties</b>	<ul style="list-style-type: none"><li>• Easy applicability and good leveling.</li><li>• High coverage and pigmentation.</li><li>• Fast drying.</li><li>• Easy sanding.</li></ul>
<b>Recommended use</b>	Sealing of carpentry and indoor furniture.
<b>Certifications</b>	
<b>Reference</b>	A1513



## Technical characteristics

	Standard	Values
<b>Solids in weight</b>	UNE EN ISO 3251	59% ±2
<b>Viscosity (Ford 4 at 20°C)</b>	UNE EN ISO 2431	120"±10
<b>Density (Kg/L)</b>	UNE EN ISO 2811-1	1.140 ± 0.020

## Catalyzation

	Standard	Values
<b>Catalyzer</b>		K0128
<b>Mixing proportion (Volume)</b>		9:1
<b>Mix solids</b>	UNE EN ISO 3251	54% ±2
<b>Mix Viscosity (Ford 4 20°C)</b>	UNE EN ISO 2431	45"±5
<b>Solvent</b>		.9130 / 10%-20%
<b>Application Viscosity (Ford 4 20°C)</b>	UNE EN ISO 2431	24" ± 2
<b>Pot life</b>	UNE EN ISO 9514	10-12 Hours

## Application characteristics

<b>Application system</b>	Aerographic and Air Mix
<b>Layer Thickness</b>	150-180 gr / m2
<b>Coats</b>	1 or 2 coats, if it's used as a self-sealer

<b>Touch dry</b>	20 to 30 minutes, depending on the thickness of the layer and the environmental conditions
<b>Sanding</b>	8-10 hours, depending on the thickness of the layer and the environmental conditions
<b>Recoatibility</b>	<ul style="list-style-type: none"> <li>• Prior sanding is necessary if repainting with a second coat of primer after 4 hours from the first application.</li> <li>• To finish with topcoat, wait 16 – 24 hours, sand and apply.</li> </ul>

**Conditions during the application process.**

In case of increase in viscosity during application, reduce with solvent .9130: BARPISOL DD 907.  
 In case of high temperature, reduce with .9020: BARPISOL RT 61.

**Process:** Once Primer 6000 White has been applied, sand and repaint with Lacacid 6000 White finish.

**Remarks**

Shake the content of the container before use.  
 Apply with good air renewal.  
 Do not store opened or started containers.  
 For toxicological standards, consult the Safety Data Sheet  
 Keep out of the reach of children

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 01-09-2020. This sheet replaces all previous versions.