



# New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

## One part, engineering sealant for immersed conditions

### Uses

Nitoseal MS600 is suitable for sealing movement joints in buildings and civil engineering structures including joints that will be subject to intermittent or permanent immersion.

Typical applications include:

- Potable water tanks
- Reservoirs
- Sewage tanks
- Sea walls\*
- Basements
- Subways
- Parapets
- Bridges
- Superstructures

\* Refer to Limitations section

### Advantages

- Recommended for use in contact with potable water
- Meets key international standards
- Resistant to aerobic and anaerobic bacteriological attack
- Exhibits excellent water resistance
- Excellent resistance to dilute acids and alkalis
- Cures to a tough, elastic rubber seal
- Accommodates continuous and pronounced cyclic movement
- High resistance to ageing, reduces physical damage due to climatic extremes
- Single component yet fast rate of cure
- Easy to apply at low temperature
- Can be applied to damp substrates
- Isocyanate free technology


### Description

Nitoseal MS600 is a one part medium modulus sealant based on hybrid silyl modified polyether technology. It has a fast rate of cure and forms a tough, highly durable and water resistant elastomer.

### Standards compliance

- ASTM C920 Type S, Grade NS, Class 25
- ISO 11600 Type F25HM
- British Standard BS 6920 : Part 1:2000



 2538	
Fosroc Ltd, Drayton Manor Business Park, Coleshill Road, Tamworth, Staffs, B78 3XN 14 DoP UK9-201	
Fosroc® Nitoseal MS600	
EN 14188:2:2004 Joint sealants for concrete pavements - cold applied	
System	1 component (s)
Type	ns-type
Class	Class A
Polymer base	MS-polymer
Extrudability	> 70ml/min.
Full immersion cure	14 days
Tack free time	2-3 hours
Resistance to flow	≤ 2mm
Change in mass/volume	≤ 5%
Resistance to hydrolysis	Shore A ≤ ± 50%
Resistance to flame	No flow, cracking, flaking, hardening, ignition
Adhesion/Cohesion properties at variable temperatures	No failure
Tensile properties at maintained extension	No failure at 23°C and -20°C
Elastic recovery	≥70 %
Artificial weathering by UV irradiation	≤ ± 20%
LEED EQc4.1 SCAQMD Rule 1168 BAAQMD Reg 8 Rule 51	Passes

# Fosroc® Nitoseal MS600

## Design criteria

Nitoseal MS600 should be applied to joints between 5 and 35mm wide. Joints which are expected to experience cyclic movements should be designed to an optimum width : depth ratio of 2:1, subject to the overriding recommended minimum sealant depths set out below: 5mm for metals, glass and other non-porous surfaces; 8mm for all porous surfaces; 20mm for joints subject to hydrostatic pressure.

To ensure that the sealant remains within its stated movement capacity (25% MAF), sealing slot widths should be designed in accordance with the recommendations of BS 6093.1993. The MovementAccommodationFactor is a figure quoted indicating the ability of a sealant to accommodate joint movement throughout the service life of that sealant, expressed as a percentage of the joint width at time of sealing.

To calculate the theoretical minimum joint width knowing the expected maximum working movement of the joint:

$$W = \frac{M}{MAF/100} + M$$

W = Joint width


M = Expected maximum working movement of joint

MAF = Movement Accommodation Factor of that sealant

## Properties

<b>Form:</b>	Smooth, non-slumping paste
<b>Colour:</b>	Grey For special colours contact Fosroc for further Information
<b>Movement Accommodation factor:</b>	25% butt joints 50% lap joints
<b>Skinning time</b>	up to 2 hours depending on ambient conditions

### Cure rate:



<b>Application</b>	5°C to 50°C
<b>Service temperature:</b>	Dry -30°C to +80°C Wet up to 40°C
<b>E-Modulus ISO 8339</b>	>0.6N/mm <sup>2</sup>
<b>Elongation ASTM D412</b>	>600%
<b>Hardness shore 'A' 20°C:</b>	32

<b>Chemical resistance:</b>	Resistant to occasional spillage of many chemicals: see limitations
<b>Biological resistance:</b>	Nitoseal MS600 has been evaluated in microbiologically active situations and has been shown to have resistance to aerobic and anaerobic conditions
<b>UV resistance:</b>	Excellent
<b>Water immersion:</b>	Nitoseal MS600 must be fully cured before permanent immersion in water

## Application instructions

Joint surfaces must be clean and free from frost. Remove all dirt, laitance, loose material and foreign matter. Remove all rust, scale and protective lacquers from metal surfaces. Removal can be achieved by rigorous wire brushing, grinding or grit blasting.

Joints in concrete should preferably be sawn. After sawing, all saw slurry must be flushed away and the joint allowed to dry.

When resealing, the existing sealant should be removed from the joint and the arris cleaned back to sound clean concrete. All debris should be removed.

Any expansion joint filler must be checked to ensure it is tightly packed and no gaps or voids exist at the base of the sealing slot before positioning a bond breaker.

The use of a bond breaker is not required in expansion joints containing cellular polyethylene joint filler such as Hydrocell XL or Expandafoam. For construction or contraction joints a bond breaker tape or back-up strip should be used.

Where a particularly neat finish is required, mask the face edges of the joint before sealing and remove immediately after tooling is completed.

## Priming

Fosroc Primer MS2 is required for all joints.

When using primer, empty the entire contents of the hardener tin into the base tin and replace the base tin lid. Mix thoroughly by shaking for at least 2 minutes. Prime the joint face using a clean, dry brush. Avoid over application of primer causing puddles in the bottom of the joint.

Nitoseal MS600 can be applied between 30 minutes and 4 hours after priming. Ensure that the primer has become touch dry before sealing.

If a joint is left unsealed for more than 4 hours, the primer should be removed by grit blasting or grinding and the joint re-primed.

The pot life of Fosroc Primer MS2 is 4 hours.

Do not split packs of Fosroc Primer MS2.



# Fosroc® Nitoseal MS600

## Application and finishing

Cut the end off the sachet and place in the Fosroc GX gun. Fit the nozzle and cut at 45 degrees at a suitable size for sealing the joint.

Extrude the sealant firmly in to the joint. Tool flush within 5 minutes of application to ensure good contact between the sealant and the substrate.

## Curing

Prior to immersion in potable water, allow to cure for 21 days at 7°C or above.

## Cleaning

Clean tools immediately after use with Fosroc Equipment Cleaner.

## Estimating

### Guide to quantities

Joint	Litres per metre run	Metre run per 600ml sachet
6 x 10	0.06	10.00
12 x 10	0.12	5.00
20 x 20	0.40	1.50
25 x 12	0.30	2.00
30 x 15	0.45	1.33

### Guide to Nitoseal MS2 Primer coverage

Linear metres per pack of primer	
Joint depth mm	Nitoseal MS2 Primer 0.75 litre pack
10	500 - 600
15	333 - 400
20	250 - 300
25	200 - 240
30	166 - 200
40	125 - 150
50	100 - 120

## Limitations

- Should not be applied at temperatures below 5°C
- Not suitable for contact with bituminous materials
- Not suitable for contact with solvents, oil or petrol
- Whilst Nitoseal MS600 has excellent adhesion to many types of residual sealant, its use should not be considered a substitute for a good standard of joint preparation
- Nitoseal MS600 must be allowed to cure for 7 days before sea water or sewage immersion. Tidal sea and river wall joints can be sealed provided this condition is met.

## Packaging

Nitoseal MS600 – 10 no x 600ml sachets per box

Fosroc Primer MS2 – 0.75 litre packs

## Storage

Shelf life of 12 months if kept in a dry store at 10 – 20°C in original unopened packaging. If stored at high temperatures and / or high humidity, the shelf life may be significantly reduced.

## Precautions

### Health and safety

Nitoseal MS600 is considered safe in normal use. For further information refer to appropriate Product Safety Data Sheet.

Fosroc Primer MS2 is highly flammable, see material safety data sheet for details.

Fosroc and Nitoseal are trademarks of Fosroc International Limited



## Fosroc Limited

Drayton Manor Business Park  
Coleshill Road, Tamworth,  
Staffordshire B78 3XN. UK

[www.fosroc.com](http://www.fosroc.com)

### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.

telephone:  
+44 0 (1827) 262222

fax:  
+44 0 (1827) 262444

email:  
[enquiryuk@fosroc.com](mailto:enquiryuk@fosroc.com)



Certificate number FM 610