



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

SIGMACOVER™ 690

DESCRIPTION

Two-component high solids aluminum pigmented polyamine cured modified epoxy primer/coating

PRINCIPAL CHARACTERISTICS

- Primer/coating designed for maintenance
- Low VOC
- Good flow properties
- Self priming coating tolerant to lower grades of steel preparation
- Compatible with most aged, good adhering coatings
- Good recoatability with epoxy and polyurethane paints
- Good curing at temperatures down to 5°C (41°F)
- Good impact and abrasion resistance
- If the substrate temperature drops below 5°C (41°F) until 0°C (32°F), the wintergrade type should be used (see 7414WG)

COLOR AND GLOSS LEVEL

- Aluminum light and dark
- Semi-gloss

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.3 kg/l (10.8 lb/US gal)
Volume solids	90 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 150.0 g/kg UK PG 6/23(92) Appendix 3: max. 198.0 g/l (approx. 1.7 lb/US gal)
Recommended dry film thickness	75 - 125 µm (3.0 - 5.0 mils) depending on system
Theoretical spreading rate	12.0 m ² /l for 75 µm (481 ft ² /US gal for 3.0 mils) 7.2 m ² /l for 125 µm (289 ft ² /US gal for 5.0 mils)
Dry to touch	4 hours
Overcoating Interval	Minimum: 12 hours Maximum: 4 months
Full cure after	5 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA - Spreading rate and film thickness
- See ADDITIONAL DATA - Overcoating intervals
- See ADDITIONAL DATA - Curing time



SIGMACOVER™ 690

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Atmospheric exposure conditions

- Steel; blast cleaned to ISO-Sa2 or power tool cleaned to ISO-St2 for good corrosion protection
- Steel with approved shop primer; sweep blasted to SPSS-Ss or power tool cleaned to SPSS-Pt2
- Existing sound coating systems; sufficiently roughened, dry and cleaned

Immersion in water

- Steel; blast cleaned to ISO-Sa2½
- Steel with approved zinc silicate shop primer; sweep blasted to SPSS-Ss or power tool cleaned to SPSS-Pt3

Substrate temperature

- Substrate temperature during application and curing should be above 5°C (41°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 77.5:22:5

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance and slower cure
- Thinner should be added after mixing the components

Induction time

None

Pot life

3 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

Air spray

Recommended thinner

THINNER 91-92

Volume of thinner

5 - 10%, depending on required thickness and application conditions

Nozzle orifice

1.8 - 2.0 mm (approx. 0.070 - 0.079 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)



SIGMACOVER™ 690

Airless spray

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 5%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.48 – 0.53 mm (0.019 – 0.021 in)

Nozzle pressure

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

Brush/roller

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 5%

Cleaning solvent

THINNER 90-53

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
75 µm (3.0 mils)	12.0 m ² /l (481 ft ² /US gal)
100 µm (4.0 mils)	9.0 m ² /l (361 ft ² /US gal)
125 µm (5.0 mils)	7.2 m ² /l (289 ft ² /US gal)

Overcoating interval for DFT up to 125 µm (5.0 mils)							
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	15°C (59°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	48 hours	36 hours	20 hours	12 hours	8 hours	6 hours
	Maximum	6 months	6 months	6 months	4 months	3 months	3 months

Notes:

- Surface should be dry and free from any contamination
- For polyurethane paints the minimum overcoating time should be raised with 50%

SIGMACOVER™ 690

Curing time for DFT up to 125 µm (5.0 mils)			
Substrate temperature	Dry to touch	Dry to handle	Full cure
5°C (41°F)	16 hours	48 hours	10 days
10°C (50°F)	9 hours	36 hours	7 days
15°C (59°F)	6 hours	20 hours	6 days
20°C (68°F)	4 hours	12 hours	5 days
30°C (86°F)	3 hours	8 hours	4 days
40°C (104°F)	2 hours	6 hours	48 hours

Note: Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)

Pot life (at application viscosity)	
Mixed product temperature	Pot life
15°C (59°F)	5 hours
20°C (68°F)	3 hours
30°C (86°F)	2 hours
40°C (104°F)	1 hour
50°C (122°F)	1 hour

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
SAFETY INDICATIONS	INFORMATION SHEET	1430
SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
DIRECTIVES FOR VENTILATION PRACTICE	INFORMATION SHEET	1434
CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490



SIGMACOVER™ 690

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

