

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND





THINNER 633

Solvent based on aliphatic hydrocarbons

- Correct solvent combination for Rust-Oleum products based on alkyd resin binder
- Highly diluting capacity

THINNER 633

DESCRIPTION

Highly diluting solvent based on aliphatic hydrocarbons, suitable for alkyd based coatings.

RECOMMENDED USE

Cleaning and/or Thinning solution for the following products:

- 569 Quick drying metal primer
- 769 Damp-proof rust primer
- 1060/1080 High build metal primer
- 7200 Floorcoat PU
- 7500 Alkythane
- 8399 Hygienic Primer

APPLICATION & THINNING: BRUSH

Can be diluted up to 10% volume

APPLICATION & THINNING: ROLLER

Can be diluted up to 10% volume

REMARKS

See the Product Data sheet of the respective product for further details.

SAFETY DATA

VOC level: 755 g/l

Remarks regarding safety: Consult Safety Data Sheet and Safety Information

printed on the can.

SHELF LIFE

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35° C.

Date issued: 07/07/2020

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V. Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T: +31 (0) 165 593 636 F: +31 (0) 165 593 600 Tor Coatings Ltd (Rust-Oleum Industria Shadon Way, Portobello Ind. Estate Birtley, Chester-le-Street DH3 2RE United Kingdom T: +44 (0)1914 113 146 F: +44 (0)1914 113 147 info@rust-oleum.eu

Rust-Oleum France S.A.:
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 90 44
F: +33(0) 130 40 99 80

N.V. Martin Mathys S.A. Kolenbergstraat 23 3545 Zelem Belgium T: +32 (0) 13 460 200 F: +32 (0) 13 460 201 info@nist-oleum.eu