

New Guard Coatings Group

A global reputation to protect.

You have acquired this data sheet from the New Guard Coatings Group.

All information listed is correct at the time of print.



uksales@newguardcoatings.com



+44 1937 586311

Global Head Office: New Guard Coatings Ltd, Sandbeck Way, Wetherby, Leeds, LS22 7DN



RUST-OLEUM®
INDUSTRIAL



769® DAMP-PROOF RUST PRIMER

Single pack primer that penetrates rust

- Requires minimal surface preparation
- Penetrates deep into the rust for optimal protection
- Expels moisture & air from the surface
- Can be applied on slightly damp surfaces
- Unique proven formula based on fish oil since 1921

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

769® DAMP-PROOF RUST PRIMER

DESCRIPTION

Single pack rust primer for direct application on slightly moist or dry metal surfaces. Proven formula since 1921!

RECOMMENDED USE

769 is specially developed to be applied on hand tool prepared sound rusted steel surfaces. Can be applied on slightly damp surfaces and provides protection under light industrial exposure conditions, if followed by a second primer 1060/1080 and/or Alkythane® 7500.

TECHNICAL DATA

Density:	1,33
Gloss Level:	Matt
Corrosion Class:	C3 average protection
Solids content in volume:	50 %
Heat Resistance:	120°C (dry heat)

DRYING TIMES AT 20°C/RH 50%

Touch dry:	4 hours
Dry to handle:	8 hours
Dry to recoat:	After 24 hours
Fully cured:	8 days

RECOMMENDED WET FILM THICKNESS

70 µm

RECOMMENDED DRY FILM THICKNESS

35 µm

THEORETICAL CONSUMPTION

14,5 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove rust scale, loose mill scale, loose rust and loose coatings by scraping and wire brushing to St 2 (ISO 8501-1: 1988), light blast cleaning or sanding. Sand previous coatings, which are in good condition to roughen the surface slightly. The surface must be clean and preferably dry during application.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

APPLICATION & THINNING: BRUSH

Dilute up to 10% volume RUST-OLEUM Thinner 633.

Use natural bristles, long hair brushes.

APPLICATION & THINNING: ROLLER

Dilute up to 10% volume RUST-OLEUM Thinner 633.

Use medium nap, polyamide 8 -12 mm rollers. Roller application may require 2 coats to achieve recommended dry film thickness.

APPLICATION & THINNING: AIRLESS SPRAY

If required, up to 5% volume RUST-OLEUM Thinner 641.

Pneumatic and electric airless equipment. Tip size: 0.013-0.015 inch Fluid pressure: 130 - 200 bar.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

10-20% volume RUST-OLEUM Thinner 641.

Gravity cup and pressure cup. Tip size: 1.2 -1.8 mm. Atomising pressure: 2 - 4 bar.

CLEANING OF EQUIPMENT / SPILLS

Use RUST-OLEUM Thinner 160 or mineral spirits.

REMARKS

Maximum dry film thickness per coat: 60 µm dry, equals 120 µm wet.

SAFETY DATA

VOC level:	375 g/l
VOC ready mix:	456 g/l
VOC category:	A/i
VOC limit:	500 g/l
Grenelle:	A+
Flashpoint:	40°C
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 30/03/2018

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Rust-Oleum UK Ltd.
PO Box 261
Chester-le-Street
DH3 9EH United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
11, rue Jules Verne - B.P. 60039
95322 St-Leu-La-Forêt Cedex
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu