



# New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND



# FASTOP MULTI SL23



07/2023 Issue 5 – REF: SL23C

## PRODUCT DESCRIPTION

FasTop Multi SL23 is a polyurethane cement self-levelling resin floor screed designed to provide heavy duty usage with resistance to thermal shock, abrasion and chemical attack in aggressive industrial environments. The system utilises universal FasTop Multi bases, hardeners and colourants in combination with a specific aggregate to provide smooth seamless matt surface with good anti-slip properties.

### ADVANTAGES

- High chemical resistance
- Resistant to hot water and steam
- Self-sealing
- Extremely hard wearing
- Good slip resistant finish
- Matt finish
- Campden BRI Tested
- HACCP certified

### RECOMMENDED USE

A wide range of industrial applications such as:

- Food manufacture and processing
- Brewing and beverage
- Pharmaceutical and chemical plant processing
- Heavy duty plant and traffic areas
- Dairies
- Commercial kitchens
- Abattoirs and meat processing

## PRODUCT DATA

<b>Volume Solids:</b>	~100%
<b>VOC:</b>	14 g/l calculated per full mixed unit
<b>Colours:</b>	Black, Blue, Buff, Dark Grey, Mid Grey, Light Grey, Green, Marigold, Red
<b>Finish:</b>	Matt
<b>Pack Size:</b>	16.1 kg
<b>Pack Weights:</b>	2.32 kg base, 0.45 kg colour, 2.22 kg hardener, 11.11 kg aggregate (16.1 kg)
<b>Mixing Ratio:</b>	As above packing weights
<b>Mixed Density:</b>	~1.90g/cm <sup>3</sup>
<b>Shelf Life:</b>	36 months (Base), 12 months (Hardener) 6 months (Aggregate)
<b>Storage:</b>	Keep out of direct sunlight. Store in a dry place, between 15°C – 30°C. Aggregates must be stored in a dry area to prevent contamination by moisture, as this will have a detrimental effect on the product.

### Typical properties at 20°C

#### Cure Times

Recoating Intervals:	N/A
Light Traffic:	12 - 16 hours
Full Traffic :	48 hours
Full Chemical Cure:	5 - 7 days

**Pot Life:** 15 minutes from mixing

*Note: All product must be used within the pot life limit, if the product is left in the container after mixing and not used, it may release hazardous fumes due to exothermic reaction.*

#### Typical Consumption:

1.9kg/m<sup>2</sup> per mm.  
Coverage rate is calculated based on a sealed and smooth surface and may vary based on the substrate roughness and other conditions.

**System Thickness:  
(Recommended)** 2 - 3 mm

**Recommended:  
Application Methods** Trowel, rake and Spike roller

## SURFACE PREPARATION

Concrete substrates must be sound with a minimum compressive strength of 25 N/mm<sup>2</sup>, a minimum tensile strength of 1.5 N/mm<sup>2</sup> and a relative humidity at the surface of no more than 75%.

It is essential that all laitance, surface sealers and curing membranes and any surface contamination, such as oil, grease and dirt, existing coatings and loose material is removed by suitable mechanised equipment. Planing or scarifying to CSP 5-7 is recommended for this product, for detailed information, refer to ICRI Guideline No.310.2R-2013.

After surface preparation, all loose debris and dirt should be removed using vacuum equipment.

Weak concrete must be removed, and local repairs carried out.

Anchorage grooves should be cut around the perimeter of the sub-floor, and terminations, e.g. doorways, around drains and at joints, to a width and depth of twice the thickness of the floor, up to a maximum of 10mm.



07/2023 Issue 5 – REF: SL23C

# FASTOP MULTI SL23



## RECOMMENDED SYSTEMS

Priming is essential for this product to ensure a sealed substrate suitable for a self-levelling FasTop screed. Apply FasTop Multi Primer by medium nap roller, brush or squeegee. Work the primer well into the surface ensuring it is fully wetted out and then roll to complete an even coating without any ponding. Two coats may be required to eliminate any dry patches and to create an even sealed surface.

The primer should be worked into and around the anchor joints, avoid filling these with resin.

A scratch coat of the product itself can be applied as a primer at a maximum of 1.5kg/m2 over the whole area except the anchor joints. For further information please refer to recommended individual product data sheets.

## MIXING AND APPLICATION

### Mixing:

Add the FasTop Multi Part A component (base) and the FasTop Multi Part D (color package) to a suitable mixing vessel and mix for 1 - 2 minutes using a low-speed electric mixer or forced action mixer until homogeneous. Add the FasTop Multi Part B (hardener) component and mix again for 1 - 2 minutes until homogeneous. Add Part C (aggregate) steadily into the mixing vessel and mix for a minimum of 3 minutes until a uniform mixture is obtained.

FasTop Multi SL23 should be applied immediately after mixing to prepared areas.

### Application

FasTop Multi SL23 When thoroughly mixed should be poured evenly over the appropriate area to be covered (monitoring rate of coverage to ensure correct depth of screed). Low floor temperatures and reduced thickness may reduce the flow properties of these products. Work out the mix rapidly and evenly over the area with a notched trowel, pin rake or similar to the appropriate thickness. Roll immediately with a spiked roller to achieve an even smooth surface and remove entrapped air. Do not re-roll later.

FasTop Multi SL23 may be applied to substrates with a surface temperature in the range of 5-20°C and a relative humidity of 40% to 90% RH, with a minimum air temperature of 8°C and no condensation. Do not pre-warm this product as working times will be substantially reduced if materials are warm.

NB: Cure times are extended at low temperatures.

See Sherwin-Williams FasTop SL23 System Guides for recommended floor systems.

## TECHNICAL INFORMATION

The following figures are obtained from laboratory tests and our experience with this product.

<b>Category Guide:</b>	FeRFA Type 5
<b>Bond Strength:</b> <b>(BS EN 13892-8:2002)</b>	>3 N/mm <sup>2</sup> (Substrate failure)
<b>Abrasion Resistance:</b> <b>(BS EN 13892-4:2002)</b>	AR 0.5 (Less than 50 microns wear)
<b>Reaction to Fire:</b> <b>(EN 13501-1:2018)</b>	Bfl-s1
<b>Compressive Strength:</b> <b>(BS EN 13892-2:2002)</b>	43 MPa
<b>Flexural Strength:</b> <b>(BS EN 13892-2:2002)</b>	26 N/mm <sup>2</sup>
<b>Tensile, Strength:</b> <b>(BS EN 6319-7:1985)</b>	7 N/mm <sup>2</sup>
<b>Impact Resistance:</b> <b>(BS EN ISO 6272-1:2011)</b>	>4 Nm
<b>Slip Resistance:</b> <b>(BS 7976-2:2002+A1:2013)</b>	Can achieve >36 (low slip potential in wet/dry conditions)
<b>Chemical Resistance:</b>	Excellent – please see separate guide or contact Sherwin-Williams

## WARRANTY

Any person or company using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk, and Sherwin-Williams can accept no liability for the performance of the product, or for any loss or damage arising out of such use.

The information detailed in this datasheet is liable to modification from time to time in the light of experience and normal product development, and before using, customers are advised to check with Sherwin-Williams, quoting the reference number, to ensure that they possess the latest issue.

## DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

## HEALTH AND SAFETY

Consult Safety Datasheet for information on safe storage and handling of this product.

Sherwin-Williams UK Limited, Protective & Marine Division  
Tower Works, Kestor Street, Bolton, BL2 2AL, United Kingdom.

T: +44 (0)1204 521771 F: +44 (0)1204 382115

W: <https://industrial.sherwin-williams.com/emeai/gb/en/resin-flooring.html>

Registered in England Reg. No. 2968830 Reg. Office: Station Lane, Witney, Oxfordshire, United Kingdom, OX28 4XR



Sherwin Williams Protective & Marine Coatings  
Tower Works, Kestor Street, Bolton, BL2 2AL, United Kingdom  
Tel: +44 (0) 1204 521771 F: +44 (0) 1204 382115

13

**BS EN 13813: SR-B3.1-AR0.5-IR>4**  
Resin coating/screed for use inside buildings as per datasheet  
**Wear resistance: AR0.5**  
**Bond strength: B3.1**  
**Impact resistance: IR>4**