



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND



**PROTECTIVE
&
MARINE
COATINGS**

Revised 11/2021 Issue 3 – REF : GPCP

**Resubind CP
PRODUCT TECHNICAL DATA**

PRODUCT DESCRIPTION

Resubind CP is a 3 component, non-pigmented, solvent-free polyurethane binder designed for car park decks, walkways and driveways. Resubind CP is designed for surface dressing with aggregates to create non-slip, hard wearing, textured floor finishes. Resubind CP systems can be used in interior or exterior car park decks on a variety of substrates to provide high wear resistant anti-slip finishes.

ADVANTAGES

- Excellent slip resistant finish
- Extremely hard wearing
- Different aggregates can be used to create various profiles
- High bond strength
- Will cure at temperatures down to 5°C
- Easy and fast to apply
- VOC Free

RECOMMENDED USE

- Intermediate Car Park Decks
- Top Car Park Decks
- Underground Car Park Decks
- Walkways around buildings and factories
- Theme Parks
- Public Pathways
- Public concourse areas
- Loading Bays
- Demarcation of non-slip areas

PRODUCT DATA

Volume Solids:	~100%
VOC:	<5 g/l calculated per full mixed unit
Colours:	Amber resin
Finish:	Textured
Flash Point:	N/A
Cleanser/Thinner:	Thinning not recommended
Pack Size:	19.5 kg
Pack Weights:	6.91 kg base/2.65 kg hardener/ Filler SL2 (10kg) (19.5 kg)
Mixing Ratio:	2.6 parts base to 1 part hardener to 3.7 parts aggregate by weight only
Mixed Density:	Approximately 1.6 g/cm ³
Shelf Life:	36 months (Base and Aggregate), 12 months (Hardener) when stored in unopened containers
Storage:	Keep out of direct sunlight. Store in a dry place, between 15°C – 20°C
Recommended Application Methods:	Squeegee, pin rake or trowel

Application at 20°C

Recoating Intervals:	6 – 8 hours or once surface has lost tackiness
Light Traffic:	6 – 8 hours
Full Traffic:	16 – 24 hours
Full Chemical Cure	7 days

Pot Life: 10 - 15minutes from mixing, based on 19.5 kg pack size

The pot life may be shorter for larger pack sizes if the product is not used within the pot life limit.

Note: All mixed product must be used within the pot life time limit, if the product is left in the container after mixing and not used, it may release hazardous fumes due to exothermic reaction.

Coverage Rate: 19.5 kg will cover 21 m² @ 500 µm or 10 m² @ 1000 µm

Coverage rate is calculated based on a sealed and smooth surface and may vary based on the substrate roughness and other conditions.

System Thickness: (Recommended) 500 – 1000 µm

The suggested thickness range is calculated based on average volume solid as a general recommendation for the specified condition and for each application may vary.



SURFACE PREPARATION

New Concrete Floors: New concrete must be clean, sound, dry, fully cured and surface laitance removed by vacuum enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm² is required.

Existing Concrete Floors: Remove all dirt, oil, grease, old product or any other surface contaminants by vacuum enclosed shot blasting, scarifying or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing and making sure all residue of detergent is washed and removed by rinsing with clean water. Local repairs should be carried out using **Resufloor Patch**.

Existing Floors (previously coated): All previous coatings and loose floor products must be removed by mechanical preparation as described in the above section and primed as specified. If the old resin flooring cannot be removed then please consult with our technical team for advice on intercoat adhesion and suitability, as it may not be compatible with the existing floor coating.

Where **Resubind CP** is applied to masonry/concrete surfaces, care must be taken to ensure that surface preparation is thorough but does not disfigure the surface.

PRIMING	APPLICATION CONDITIONS										
<p>Open and porous substrates will require priming with Resuprime PU on dry substrates only with less than 75% ERH reading.</p> <p>Where the Relative Humidity of a substrate exceeds 75% ERH please refer to the table below for required number of coats to achieve proper moisture tolerance.</p> <p>ERH% Required Coating Thickness</p> <table style="width: 100%; border: none;"> <tr> <td style="width: 15%;">75-85</td> <td>1 coat of Resuprime MVT at 200 µm per coat</td> </tr> <tr> <td>85-92</td> <td>2 coats of Resuprime MVT at 200 µm per coat</td> </tr> <tr> <td>92-97</td> <td>3 coats of Resuprime MVT at 200 µm per coat</td> </tr> </table> <p><i>For further information please refer to recommended individual product data sheets.</i></p>	75-85	1 coat of Resuprime MVT at 200 µm per coat	85-92	2 coats of Resuprime MVT at 200 µm per coat	92-97	3 coats of Resuprime MVT at 200 µm per coat	<p>The ambient temperatures of the areas should not be allowed to fall below 15°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature must be above 10°C. Where possible it is recommended that the application area is heated to a minimum temperature of 15°C ideally to allow the ambient and substrate temperature to stabilise prior to the installation.</p> <p>The surface should be protected from temperatures of less than 5°C and moisture in the early stages of cure. This could adversely affect the flow, levelling and surface finish of Resubind CP.</p>				
75-85	1 coat of Resuprime MVT at 200 µm per coat										
85-92	2 coats of Resuprime MVT at 200 µm per coat										
92-97	3 coats of Resuprime MVT at 200 µm per coat										
MIXING & APPLICATION	TECHNICAL INFORMATION										
<p>The mixed unit should be applied immediately with a squeegee or pin rake. This is best achieved by the application of smooth even pressure with the compound poured over the correct coverage rate after fixing the stop ends to control the flow of the material. Then roll the area with a spiked roller to achieve an even smooth surface and remove entrapped air. Do not re-roll the area later than 10 mins after application. The surface should then be dressed with the selected aggregate at a rate of approximately 2-3 Kg/m².</p> <p>Pre-mix the base component to a uniform colour, then mix the entire contents of base with the hardener. If a separate mixing bucket is being used ensure all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately one to two minutes until the two components have fully combined then add the aggregate slowly. Mix for a further 1-2 minutes until the aggregate has fully combined and there are no lumps.</p>	<p>The following figures are obtained from laboratory tests and our experience with this product.</p> <table style="width: 100%; border: none;"> <tr> <td style="width: 30%;">Category Guide:</td> <td>FerFA Category 4</td> </tr> <tr> <td>Temperature Resistance:</td> <td>Tolerant of temperatures up to 60°C</td> </tr> <tr> <td>Abrasion Resistance: (BS EN 13892-4:2002)</td> <td>AR 0.5 (Less than 50 microns wear)</td> </tr> <tr> <td>Bond Strength: (BS EN 13892-8:2002)</td> <td>>3 N/mm² (Substrate failure)</td> </tr> <tr> <td>Impact Resistance: (BS EN 1504-2:2004)</td> <td>Class II</td> </tr> </table>	Category Guide:	FerFA Category 4	Temperature Resistance:	Tolerant of temperatures up to 60°C	Abrasion Resistance: (BS EN 13892-4:2002)	AR 0.5 (Less than 50 microns wear)	Bond Strength: (BS EN 13892-8:2002)	>3 N/mm ² (Substrate failure)	Impact Resistance: (BS EN 1504-2:2004)	Class II
Category Guide:	FerFA Category 4										
Temperature Resistance:	Tolerant of temperatures up to 60°C										
Abrasion Resistance: (BS EN 13892-4:2002)	AR 0.5 (Less than 50 microns wear)										
Bond Strength: (BS EN 13892-8:2002)	>3 N/mm ² (Substrate failure)										
Impact Resistance: (BS EN 1504-2:2004)	Class II										

CE MARK

	CE							
	<p>Sherwin-Williams Protective & Marine Tower Works, Kestor Street, Bolton, BL2 2AL, United Kingdom Tel: +44 (0) 1204 521771 F: +44 (0) 1204 38211516</p>							
	<p>13</p> <p>BSEN 13813 SR B 3.0 - AR 0.5 - IR>4 Resin coating/screed for use inside buildings as per data sheet</p> <table style="width: 100%; border: none;"> <tr> <td style="width: 50%;">Wear resistance:</td> <td>AR 0.5</td> </tr> <tr> <td>Bond strength:</td> <td>B 3.0</td> </tr> <tr> <td>Impact resistance:</td> <td>IR > 4</td> </tr> </table>	Wear resistance:	AR 0.5	Bond strength:	B 3.0	Impact resistance:	IR > 4	
Wear resistance:	AR 0.5							
Bond strength:	B 3.0							
Impact resistance:	IR > 4							

WARRANTY

Any person or company using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk, and Sherwin-Williams can accept no liability for the performance of the product, or for any loss or damage arising out of such use.

The information detailed in this datasheet is liable to modification from time to time in the light of experience and normal product development, and before using, customers are advised to check with Sherwin-Williams, quoting the reference number, to ensure that they possess the latest issue.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

HEALTH AND SAFETY

Consult Product Health and Safety Datasheet for information on safe storage, handling and application of this product.

Sherwin-Williams Protective & Marine Coatings, Tower Works, Kestor Street, Bolton, Lancashire BL2 2AL United Kingdom

T: 01204 521 771 E: sales.uk@sherwin.com www.resinflooring.sherwin.eu

Registered in England 1659941 VAT GB 373 485624

www.sherwin-williams.com/protectiveEMEA

This datasheet is specifically subject to the disclaimer which can be found at: <http://protectiveemea.sherwin-williams.com/Home/Disclaimer>